

TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH19009596S2

Applicant: PLAN CREATIONS CO., LTD.
8 MOO 8, TRANG-PALIAN RD.,
YANTAKAO, TRANG, THAILAND 92140
ATTN: K.NARONG, K.SUPAPORN

Date: Dec 23, 2019
**This report supersedes
The previous report
Date Aug 21, 2019**

Sample description:

| | |
|---------------------------------|--------------------------|
| Quantity of sample: | One (1) set |
| Sample description: | Wooden toy |
| Date sample received: | July 31, 2019 |
| Date information received: | August 19, 2019 |
| Date sample resubmitted: | December 12, 2019 |

Client Information:

One (1) set of submitted sample said to be BAKERY STAND SET

| | |
|--------------|------------------|
| Item Name: | BAKERY STAND SET |
| Item Number: | 3489 |



BKKH19009596S2

Test conducted:

As requested by the applicant, for details please refer to attached page(s)

To be continued

For and on behalf of :
Intertek Testing Services (Thailand) Ltd.,
Hardlines Laboratory


Ladtaka Wongwiboonporn
Laboratory Manager
Hardlines Department

TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.



Number: BKKH19009596S2

Conclusion:

| <u>Tested samples</u> | <u>Standard</u> | <u>Result</u> |
|-----------------------|--|---------------|
| Submitted sample | U.S. ASTM F963-17 for Physical and mechanical tests | Pass |
| | U.S. ASTM F963-17 for Flammability test of materials other than textile materials | Pass |
| | U.S. ASTM F963-17 for Heavy elements Test | Pass |
| | <u>Standard - U.S. CFR title 16</u> (CPSC regulations) Part 1303 total Lead content | Pass |
| | <u>Standard</u> U.S. Consumer product safety improvement Act 2008(H.R. 4040) Title I, Section 101 For total lead content in surface coating | Pass |
| | U.S. Consumer product safety improvement Act 2008(H.R. 4040) Title I, Section 101 For total lead content in non-surface coating material (substrate) | Pass |
| | US 16 CFR Part 1307 for Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates | Pass |
| | Phthalate Content Requirement base on the California Proposition 65 | Pass |
| | Illinois Lead Poisoning Prevention Act 410 ILCS 45 section 6 (public act 095-1019) | Pass |

Remark: As requested by the applicant, the test was conducted only on components listed in this report. Other components were not tested.



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH19009596S2

Remark:

The chemical test results was not conducted on the below components of samples. Applicant claimed the components were tested on our previous test report.

| <u>Components</u> | <u>Report No.</u> | <u>Date</u> |
|----------------------------------|-------------------|--------------|
| <u>ASTM F963-17: Heavy metal</u> | | |
| WHITE COATING ON WOOD | BKKH19007793S1 | Jul 15, 2019 |
| LACQUER COATING ON WOOD | BKKH19007792S1 | Jul 15, 2019 |
| RED COATING ON WOOD | BKKH19007790S1 | Jul 15, 2019 |
| BROWN COATING ON WOOD | BKKH19007792S1 | Jul 15, 2019 |
| YELLOW COATING ON WOOD | BKKH19007790S1 | Jul 15, 2019 |
| WHITE COATING ON WOOD | BKKH19007793S1 | Jul 15, 2019 |
| BLACK COATING ON WOOD | BKKH19007793S1 | Jul 15, 2019 |
| BROWN COATING ON WOOD | BKKH19007791S1 | Jul 15, 2019 |
| PINK COATING ON WOOD | BKKH19007790S1 | Jul 15, 2019 |
| LIGHT ORANGE COATING ON WOOD | BKKH19009836 | Aug 15, 2019 |
| BLUE COATING ON WOOD | BKKH19008028S1 | Jul 18, 2019 |
| LIGHT YELLOW COATING ON WOOD | BKKH19009836 | Aug 15, 2019 |
| BROWN PLASTIC JOINT | BKKH19009590S1 | Aug 19, 2019 |
| <u>Lead in surface coating</u> | | |
| WHITE COATING ON WOOD | BKKH19007793S1 | Jul 15, 2019 |
| LACQUER COATING ON WOOD | BKKH19007792S1 | Jul 15, 2019 |
| RED COATING ON WOOD | BKKH19007790S1 | Jul 15, 2019 |
| BROWN COATING ON WOOD | BKKH19007792S1 | Jul 15, 2019 |
| YELLOW COATING ON WOOD | BKKH19007790S1 | Jul 15, 2019 |
| WHITE COATING ON WOOD | BKKH19007793S1 | Jul 15, 2019 |
| BLACK COATING ON WOOD | BKKH19007793S1 | Jul 15, 2019 |
| BROWN COATING ON WOOD | BKKH19007791S1 | Jul 15, 2019 |
| PINK COATING ON WOOD | BKKH19007790S1 | Jul 15, 2019 |
| LIGHT ORANGE COATING ON WOOD | BKKH19009836 | Aug 15, 2019 |
| BLUE COATING ON WOOD | BKKH19008028S1 | Jul 18, 2019 |
| LIGHT YELLOW COATING ON WOOD | BKKH19009836 | Aug 15, 2019 |
| <u>Lead in substrate</u> | | |
| BROWN PLASTIC JOINT | BKKH19009590S1 | Aug 19, 2019 |



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.



Number: BKKH19009596S2

| <u>Components</u> | <u>Report No.</u> | <u>Date</u> |
|------------------------------|-------------------|--------------|
| <u>Phthalate content</u> | | |
| WHITE COATING ON WOOD | BKKH19007793S1 | Jul 15, 2019 |
| LACQUER COATING ON WOOD | BKKH19007792S1 | Jul 15, 2019 |
| RED COATING ON WOOD | BKKH19007790S1 | Jul 15, 2019 |
| BROWN COATING ON WOOD | BKKH19007792S1 | Jul 15, 2019 |
| BROWN PLASTIC JOINT | BKKH19009590S1 | Aug 19, 2019 |
| YELLOW COATING ON WOOD | BKKH19007790S1 | Jul 15, 2019 |
| WHITE COATING ON WOOD | BKKH19007793S1 | Jul 15, 2019 |
| BLACK COATING ON WOOD | BKKH19007793S1 | Jul 15, 2019 |
| BROWN COATING ON WOOD | BKKH19007791S1 | Jul 15, 2019 |
| PINK COATING ON WOOD | BKKH19007790S1 | Jul 15, 2019 |
| LIGHT ORANGE COATING ON WOOD | BKKH19009836 | Aug 15, 2019 |
| BLUE COATING ON WOOD | BKKH19008028S1 | Jul 18, 2019 |
| LIGHT YELLOW COATING ON WOOD | BKKH19009836 | Aug 15, 2019 |



TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH19009596S2

Test conducted:

1 Physical And Mechanical Tests

Test Standard : ASTM Standard Consumer Safety Specification for Toy Safety F963-17.

Age group for testing : For age over 2 years.

The submitted samples were undergone the use and abuse tests in accordance with the Federal Hazardous Substances Act (FHSA), Title 16, Code of Federal Regulations : -

| <u>Test</u> | <u>FHSA</u> | <u>Parameter</u> |
|------------------|--------------------|------------------|
| Drop test | Section 1500.53(b) | 4 x 3.0 ft |
| Torque test | Section 1500.53(e) | 4 in-lbf |
| Tension test | Section 1500.53(f) | 15 lbf |
| Compression test | Section 1500.53(g) | 30 lbf |

| <u>Clause</u> | <u>Testing items</u> | <u>Assessment</u> |
|---|--|-------------------|
| 4.1 | Material quality | P |
| 4.5 | Sound-producing toys | NA |
| 4.6.1 | Toys intended for children under 36 months (small objects) | NA |
| 4.6.2 [▲] | Mouth-actuated toys | NA |
| 4.6.3 | Toys and games for 36 months to 72 months (small part warning) | NA |
| 4.7 | Accessible edges | P |
| 4.8 | Projections | P |
| 4.9 | Accessible points | P |
| 4.10 | Wires or rods | NA |
| 4.11 | Nails and fasteners | NA |
| 4.12 | Plastic film | NA |
| 4.13 | Folding mechanisms and hinges | NA |
| 4.14 | Cords, straps and elastics | NA |
| 4.15 | Stability and over-load requirements | NA |
| 4.16 | Confined spaces | NA |
| 4.17 | Wheels, tires and axles | NA |
| 4.18 | Holes, clearance, and accessibility of mechanisms | NA |
| 4.19 | Simulated protective devices | NA |
| 4.20 (excluding 4.20.1 [▲]) | Pacifiers | NA |
| 4.21 | Projectile toys | NA |
| 4.22 | Teethers and teething toys | NA |

TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH19009596S2

Test conducted:

| Clause | Testing items | Assessment |
|--|--|------------|
| 4.23 | Rattles | NA |
| 4.24 | Squeeze toys | NA |
| 4.25 (excluding 4.25.10, 4.25.11 [▲]) | Battery-operated toys | NA |
| 4.26 | Toys intended to be attached to a crib or playpen | NA |
| 4.27 | Stuffed and beanbag-type toys | NA |
| 4.28 | Stroller and carriage toys | NA |
| 4.29 | Art materials | NA |
| 4.30 | Toy gun marking | NA |
| 4.31 | Balloons | NA |
| 4.32 | Certain toys with nearly spherical ends | NA |
| 4.33 | Marbles | NA |
| 4.34 | Balls | NA |
| 4.35 | Pompoms | NA |
| 4.36 | Hemispheric-shaped objects | NA |
| 4.37 [▲] | Yoyo elastic tether toys | NA |
| 4.38 | Magnets | NA |
| 4.39 | Jaw entrapment in handles and steering wheels | NA |
| 4.40 | Expanding materials | NA |
| 4.41 | Toy chests | NA |
| 5 | Labelling requirement | P |
| 6 | Instructional literature | P |
| 7 | Producer's markings - name of producer (toy and package) - address (package) | Yes Yes |

Remark : P = Pass NA = Not applicable

▲ = Tested items are not included in the TISI Accreditation

The submitted samples were undergone the tests in accordance with clause 8.5 through clause 8.17 and 8.19 through 8.26 on normal use, abuse and specific tests for different types of toys whichever is applicable.

Testing period : July 31, 2019 to **December 14, 2019**

2 Flammability Test

Test Standard : Clause 4.2 of the ASTM Standard Consumer Safety Specification for Toy Safety F963-17.

Results : Did not ignite

Testing period : July 31, 2019 to August 05, 2019



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH19009596S2

Test conducted:

3 Heavy Elements Analysis

As per clause 4.3.5.1(2) of the ASTM Standard Consumer Safety Specification on Toy Safety F963-17, acid extraction method was used and heavy elements migration content were determined by ICP-OES analysis.

| | (1) | (2) | Result | (4) | (5) | LOD | LOQ | Limit mg/kg |
|--------------------|-----|-----|--------|-----|-----|-------|-------|-------------|
| | | | mg/kg | | | mg/kg | mg/kg | |
| Sol. Barium (Ba) | ND | ND | ND | 40 | ND | 1 | 5 | 1000 |
| Sol. Lead (Pb) | ND | ND | ND | ND | ND | 1 | 5 | 90 |
| Sol. Cadmium (Cd) | ND | ND | ND | ND | ND | 1 | 5 | 75 |
| Sol. Antimony (Sb) | ND | ND | ND | ND | ND | 2 | 5 | 60 |
| Sol. Selenium (Se) | ND | ND | ND | ND | ND | 1 | 5 | 500 |
| Sol. Chromium (Cr) | ND | ND | ND | ND | ND | 2 | 5 | 60 |
| Sol. Mercury (Hg) | ND | ND | ND | ND | ND | 1 | 5 | 60 |
| Sol. Arsenic (As) | ND | ND | ND | ND | ND | 2 | 5 | 25 |

Remark: Sol. = Soluble
mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
LOD = Limit of Detection LOQ = Limit of Quantitation
ND = Not detected (Less than LOD)

Tested components:

- | | | |
|-------------------------------|-------|----------------|
| (1) = WHITE COATING ON WOOD | Refer | BKKH19007793S1 |
| (2) = LACQUER COATING ON WOOD | Refer | BKKH19007792S1 |
| (3) = RED COATING ON WOOD | Refer | BKKH19007790S1 |
| (4) = BROWN COATING ON WOOD | Refer | BKKH19007792S1 |
| (5) = YELLOW COATING ON WOOD | Refer | BKKH19007790S1 |

Note: The results of soluble toxic elements were adjusted by subtracting the analytical correction factor.



TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH19009596S2

Test conducted:

Heavy Elements Analysis

As per clause 4.3.5.1(2) of the ASTM Standard Consumer Safety Specification on Toy Safety F963-17, acid extraction method was used and heavy elements migration content were determined by ICP-OES analysis.

| | (6) | (7) | Result mg/kg (8) | (9) | (10) | LOD mg/kg | LOQ mg/kg | Limit mg/kg |
|--------------------|-----|-----|------------------------|-----|------|--------------|--------------|-------------|
| Sol. Barium (Ba) | ND | ND | ND | ND | <5 | 1 | 5 | 1000 |
| Sol. Lead (Pb) | ND | ND | ND | ND | <5 | 1 | 5 | 90 |
| Sol. Cadmium (Cd) | ND | ND | ND | ND | ND | 1 | 5 | 75 |
| Sol. Antimony (Sb) | ND | ND | ND | ND | ND | 2 | 5 | 60 |
| Sol. Selenium (Se) | ND | ND | ND | ND | ND | 1 | 5 | 500 |
| Sol. Chromium (Cr) | ND | ND | ND | ND | ND | 2 | 5 | 60 |
| Sol. Mercury (Hg) | ND | ND | ND | ND | ND | 1 | 5 | 60 |
| Sol. Arsenic (As) | ND | ND | ND | ND | ND | 2 | 5 | 25 |

Remark: Sol. = Soluble
mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
LOD = Limit of Detection LOQ = Limit of Quantitation
ND = Not detected (Less than LOD) < = Less than

Tested components:

| | | |
|-------------------------------------|-------|----------------|
| (6) = WHITE COATING ON WOOD | Refer | BKKH19007793S1 |
| (7) = BLACK COATING ON WOOD | Refer | BKKH19007793S1 |
| (8) = BROWN COATING ON WOOD | Refer | BKKH19007791S1 |
| (9) = PINK COATING ON WOOD | Refer | BKKH19007790S1 |
| (10) = LIGHT ORANGE COATING ON WOOD | Refer | BKKH19009836 |

Note: The results of soluble toxic elements were adjusted by subtracting the analytical correction factor.



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH19009596S2

Test conducted:

Heavy Elements Analysis

As per clause 4.3.5.1(2) of the ASTM Standard Consumer Safety Specification on Toy Safety F963-17, acid extraction method was used and heavy elements migration content were determined by ICP-OES analysis.

| | <u>Result</u> | | <u>LOD</u> | <u>LOQ</u> | <u>Limit mg/kg</u> |
|--------------------|---------------|------|--------------|--------------|--------------------|
| | <u>mg/kg</u> | | <u>mg/kg</u> | <u>mg/kg</u> | |
| | (11) | (12) | | | |
| Sol. Barium (Ba) | ND | ND | 1 | 5 | 1000 |
| Sol. Lead (Pb) | ND | ND | 1 | 5 | 90 |
| Sol. Cadmium (Cd) | ND | ND | 1 | 5 | 75 |
| Sol. Antimony (Sb) | ND | ND | 2 | 5 | 60 |
| Sol. Selenium (Se) | ND | ND | 1 | 5 | 500 |
| Sol. Chromium (Cr) | ND | ND | 2 | 5 | 60 |
| Sol. Mercury (Hg) | ND | ND | 1 | 5 | 60 |
| Sol. Arsenic (As) | ND | ND | 2 | 5 | 25 |

Remark: Sol. = Soluble
 mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
 LOD = Limit of Detection LOQ = Limit of Quantitation
 ND = Not detected (Less than LOD)

Tested components:

- (11) = BLUE COATING ON WOOD Refer BKKH19008028S1
 (12) = LIGHT YELLOW COATING ON WOOD Refer BKKH19009836

Note: The results of soluble toxic elements were adjusted by subtracting the analytical correction factor.



TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH19009596S2

Test conducted:

Heavy Elements Analysis

As per clause 4.3.5.2(2)(b) of the ASTM Standard Consumer Safety Specification on Toy Safety F963-17, acid extraction method was used and heavy elements migration content were determined by ICP-OES analysis.

| | Result mg/kg | LOD mg/kg | LOQ mg/kg | Limit mg/kg |
|--------------------|-----------------|--------------|--------------|-------------|
| (13) | | | | |
| Sol. Barium (Ba) | ND | 1 | 5 | 1000 |
| Sol. Lead (Pb) | ND | 1 | 5 | 90 |
| Sol. Cadmium (Cd) | ND | 1 | 5 | 75 |
| Sol. Antimony (Sb) | ND | 2 | 5 | 60 |
| Sol. Selenium (Se) | ND | 1 | 5 | 500 |
| Sol. Chromium (Cr) | ND | 2 | 5 | 60 |
| Sol. Mercury (Hg) | ND | 1 | 5 | 60 |
| Sol. Arsenic (As) | ND | 2 | 5 | 25 |

Remark:

Sol. = Soluble
mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
LOD = Limit of Detection LOQ = Limit of Quantitation
ND = Not detected (Less than LOD)

Tested components:

(13) = BROWN PLASTIC JOINT

Refer BKKH19009590S1

Note: The results of soluble toxic elements were adjusted by subtracting the analytical correction factor.



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH19009596S2

Test conducted:

Total Lead (Pb) Content

As per clause 4.3.5.2(2)(a) of the ASTM Standard Consumer Safety Specification on Toy Safety F963-17, test method CPSC-CH-E1001-08.3:2012, CPSC-CH-E1002-08.3:2012 were used and total Lead content was determined by ICP-OES analysis.

(II) Non-surface coating


| <u>Tested Component</u> | <u>Result</u> <u>mg/kg</u> | <u>LOD</u> <u>(mg/kg)</u> | <u>LOQ</u> <u>(mg/kg)</u> | <u>Limit</u> <u>(mg/kg)</u> |
|-------------------------|-------------------------------|------------------------------|------------------------------|--------------------------------|
| (13) | ND | 1 | 13 | 100 |

Remark: mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
 LOD = Limit of Detection LOQ = Limit of Quantitation
 ND = Not detected (Less than LOD)

Tested components:

(13) = BROWN PLASTIC JOINT

Refer BKKH19009590S1



TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH19009596S2

Test conducted:

4 Total Lead (Pb) content▲

As per U.S. Code of Federal Regulations title 16 Part 1303. Acid digestion method was used and total Lead content was determined by Inductively Couple Plasma Optical Emission Spectrometry.

Table with 5 columns: Tested component, Result %, LOD %, LOQ %, Limit %. Rows 1-12 showing ND results for various components.

Remark: % = percentage, LOD = Limit of Detection, ND = Not detected (Less than LOD), ▲ = Tested items are not included in the TISI Accreditation

Tested components:

- List of 12 tested components (e.g., WHITE COATING ON WOOD) with corresponding reference numbers (e.g., BKKH19007793S1).



TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH19009596S2

Test conducted:

5 Total lead (Pb) content in surface coating
As per U.S. Consumer Product Safety Improvement Act of 2008 (H.R. 4040), Title I, Section 101 for children's products containing Lead, CPSC-CH-E1003-09.1:2011 method was used and total Lead content was determined by Inductively Couple Plasma Optical Emission Spectrometry.

| <u>Tested component</u> | <u>Result</u> <u>mg/kg</u> | <u>LOD</u> <u>mg/kg</u> | <u>LOQ</u> <u>mg/kg</u> | <u>Limit mg/kg</u> |
|-------------------------|-------------------------------|----------------------------|----------------------------|--------------------|
| (1) | ND | 2 | 13 | 90 |
| (2) | ND | 2 | 13 | 90 |
| (3) | ND | 2 | 13 | 90 |
| (4) | ND | 2 | 13 | 90 |
| (5) | ND | 2 | 13 | 90 |
| (6) | ND | 2 | 13 | 90 |
| (7) | ND | 2 | 13 | 90 |
| (8) | ND | 2 | 13 | 90 |
| (9) | ND | 2 | 13 | 90 |
| (10) | <13 | 2 | 13 | 90 |
| (11) | ND | 2 | 13 | 90 |
| (12) | ND | 2 | 13 | 90 |

Remark: mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
LOD = Limit of Detection LOD = Limit of Quantitation
ND = Not detected (Less than LOD) < = Less than

Tested components:

- | | |
|-------------------------------------|----------------------|
| (1) = WHITE COATING ON WOOD | Refer BKKH19007793S1 |
| (2) = LACQUER COATING ON WOOD | Refer BKKH19007792S1 |
| (3) = RED COATING ON WOOD | Refer BKKH19007790S1 |
| (4) = BROWN COATING ON WOOD | Refer BKKH19007792S1 |
| (5) = YELLOW COATING ON WOOD | Refer BKKH19007790S1 |
| (6) = WHITE COATING ON WOOD | Refer BKKH19007793S1 |
| (7) = BLACK COATING ON WOOD | Refer BKKH19007793S1 |
| (8) = BROWN COATING ON WOOD | Refer BKKH19007791S1 |
| (9) = PINK COATING ON WOOD | Refer BKKH19007790S1 |
| (10) = LIGHT ORANGE COATING ON WOOD | Refer BKKH19009836 |
| (11) = BLUE COATING ON WOOD | Refer BKKH19008028S1 |
| (12) = LIGHT YELLOW COATING ON WOOD | Refer BKKH19009836 |



TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.



Number: BKKH19009596S2

Test conducted:

6 Total lead (Pb) content in substrate material- non-metal children's product
As per U.S. Consumer product safety improvement Act of 2008 (H.R. 4040), Title I, Section 101 for children's products containing lead, CPSC-CH-E1002-08.3:2012 method was used and total lead content was determined by Inductively Couple Plasma Optical Emission Spectrometry.

| <u>Tested component</u> | <u>Result</u> | <u>LOD</u> | <u>LOQ</u> | <u>Limit mg/kg</u> |
|-------------------------|---------------|--------------|--------------|--------------------|
| | <u>mg/kg</u> | <u>mg/kg</u> | <u>mg/kg</u> | |
| (1) | ND | 1 | 13 | 100 |

Remark: mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
 LOD = Limit of Detection
 LOQ = Limit of Quantitation
 ND = Not detected (Less than LOD)

Tested components:

(1) = BROWN PLASTIC JOINT

Refer BKKH19009590S1



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH19009596S2

Test conducted:

7 Phthalate content

As per CPSC-CH-C1001-09.3:2010 and U.S. Consumer Product Safety Improvement Act 2008 (H.R. 4040), Title I, Section 108 requirement on Phthalates, solvent extraction method was used and Phthalate content was determined by Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

| | <u>Result</u> | | | | | <u>LOD</u> | <u>LOQ</u> | <u>(16CFR1307)</u> | <u>NPR</u> |
|-----------------------------------|---------------|-----|-----|-----|-----|------------|------------|--------------------|------------|
| | (1) | (2) | (3) | (4) | (5) | (%, w/w) | (%, w/w) | Limit (%, w/w) | (%, w/w) |
| Dibutyl Phthalate (DBP) | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 | 0.1 |
| Di(2-ethylhexyl) phthalate (DEHP) | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 | 0.1 |
| Benzyl butyl Phthalate (BBP) | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 | 0.1 |
| Di-iso-nonyl Phthalate (DINP) | ND | ND | ND | ND | ND | 0.0015 | 0.0090 | 0.1 | 0.1 |
| Di-n-octyl Phthalate (DNOP) | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | -- | -- |
| Di-iso-decyl Phthalate (DIDP) | ND | ND | ND | ND | ND | 0.0015 | 0.0090 | -- | -- |
| Di-isobutyl phthalate (DIBP)▲ | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 | 0.1 |
| Di-n-pentyl phthalate (DPENP)▲ | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 | 0.1 |
| Di-n-hexyl phthalate (DHEXP)▲ | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 | 0.1 |
| Di-cyclohexyl phthalate (DCHP)▲ | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 | 0.1 |
| Diisooctyl phthalate (DIOP)▲ | ND | ND | ND | ND | ND | 0.0015 | 0.0090 | -- | -- |

Remark : The above limit was quoted according to US 16 CFR Part 1307 for Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates except the Phthalate no.5-6,11 was conducted as per applicant requested only.

- NPR = Notice of proposed rulemaking
- %, w/w = Percentage weight by weight
- LOD = Limit of Detection
- LOQ = Limit of Quantitation
- ND = Not detected (Less than LOD)
- ▲ = Tested items are not included in the TISI Accreditation

Tested components:

| | | |
|-------------------------------|-------|----------------|
| (1) = WHITE COATING ON WOOD | Refer | BKKH19007793S1 |
| (2) = LACQUER COATING ON WOOD | Refer | BKKH19007792S1 |
| (3) = RED COATING ON WOOD | Refer | BKKH19007790S1 |
| (4) = BROWN COATING ON WOOD | Refer | BKKH19007792S1 |
| (5) = BROWN PLASTIC JOINT | Refer | BKKH19009590S1 |



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH19009596S2

Test conducted:

Phthalate content

As per CPSC-CH-C1001-09.3:2010 and U.S. Consumer Product Safety Improvement Act 2008 (H.R. 4040), Title I, Section 108 requirement on Phthalates, solvent extraction method was used and Phthalate content was determined by Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

| | <u>Result</u> | | | | | <u>LOD</u> | <u>LOQ</u> | <u>(16CFR1307)</u> | <u>NPR</u> |
|-----------------------------------|-----------------|-----|-----|-----|------|-----------------|-----------------|-----------------------|-----------------|
| | <u>(%, w/w)</u> | | | | | <u>(%, w/w)</u> | <u>(%, w/w)</u> | <u>Limit (%, w/w)</u> | <u>(%, w/w)</u> |
| | (6) | (7) | (8) | (9) | (10) | | | | |
| Dibutyl Phthalate (DBP) | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 | 0.1 |
| Di(2-ethylhexyl) phthalate (DEHP) | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 | 0.1 |
| Benzyl butyl Phthalate (BBP) | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 | 0.1 |
| Di-iso-nonyl Phthalate (DINP) | ND | ND | ND | ND | ND | 0.0015 | 0.0090 | 0.1 | 0.1 |
| Di-n-octyl Phthalate (DNOP) | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | -- | -- |
| Di-iso-decyl Phthalate (DIDP) | ND | ND | ND | ND | ND | 0.0015 | 0.0090 | -- | -- |
| Di-isobutyl phthalate (DIBP)▲ | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 | 0.1 |
| Di-n-pentyl phthalate (DPENP)▲ | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 | 0.1 |
| Di-n-hexyl phthalate (DHEXP)▲ | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 | 0.1 |
| Di-cyclohexyl phthalate (DCHP)▲ | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 | 0.1 |
| Diisooctyl phthalate (DIOP)▲ | ND | ND | ND | ND | ND | 0.0015 | 0.0090 | -- | -- |

Remark : The above limit was quoted according to US 16 CFR Part 1307 for Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates except the Phthalate no.5-6,11 was conducted as per applicant requested only.

- NPR = Notice of proposed rulemaking
- %, w/w = Percentage weight by weight
- LOD = Limit of Detection
- LOQ = Limit of Quantitation
- ND = Not detected (Less than LOD)
- ▲ = Tested items are not included in the TISI Accreditation

Tested components:

| | | |
|------------------------------|-------|----------------|
| (6) = YELLOW COATING ON WOOD | Refer | BKKH19007790S1 |
| (7) = WHITE COATING ON WOOD | Refer | BKKH19007793S1 |
| (8) = BLACK COATING ON WOOD | Refer | BKKH19007793S1 |
| (9) = BROWN COATING ON WOOD | Refer | BKKH19007791S1 |
| (10) = PINK COATING ON WOOD | Refer | BKKH19007790S1 |



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH19009596S2

Test conducted:

Phthalate content

As per CPSC-CH-C1001-09.3:2010 and U.S. Consumer Product Safety Improvement Act 2008 (H.R. 4040), Title I, Section 108 requirement on Phthalates, solvent extraction method was used and Phthalate content was determined by Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

| | <u>Result</u> | | | <u>LOD</u> | <u>LOQ</u> | <u>(16CFR1307)</u> | <u>NPR</u> |
|---|-----------------|------|------|-----------------|-----------------|-----------------------|-----------------|
| | <u>(%, w/w)</u> | | | <u>(%, w/w)</u> | <u>(%, w/w)</u> | <u>Limit (%, w/w)</u> | <u>(%, w/w)</u> |
| | (11) | (12) | (13) | | | | |
| Dibutyl Phthalate (DBP) | ND | ND | ND | 0.0015 | 0.0030 | 0.1 | 0.1 |
| Di(2-ethylhexyl) phthalate (DEHP) | ND | ND | ND | 0.0015 | 0.0030 | 0.1 | 0.1 |
| Benzyl butyl Phthalate (BBP) | ND | ND | ND | 0.0015 | 0.0030 | 0.1 | 0.1 |
| Di-iso-nonyl Phthalate (DINP) | ND | ND | ND | 0.0015 | 0.0090 | 0.1 | 0.1 |
| Di-n-octyl Phthalate (DNOP) | ND | ND | ND | 0.0015 | 0.0030 | -- | -- |
| Di-iso-decyl Phthalate (DIDP) | ND | ND | ND | 0.0015 | 0.0090 | -- | -- |
| Di-isobutyl phthalate (DIBP) [▲] | ND | ND | ND | 0.0015 | 0.0030 | 0.1 | 0.1 |
| Di-n-pentyl phthalate (DPENP) [▲] | ND | ND | ND | 0.0015 | 0.0030 | 0.1 | 0.1 |
| Di-n-hexyl phthalate (DHEXP) [▲] | ND | ND | ND | 0.0015 | 0.0030 | 0.1 | 0.1 |
| Di-cyclohexyl phthalate (DCHP) [▲] | ND | ND | ND | 0.0015 | 0.0030 | 0.1 | 0.1 |
| Diisooctyl phthalate (DIOP) [▲] | ND | ND | ND | 0.0015 | 0.0090 | -- | -- |

Remark : The above limit was quoted according to US 16 CFR Part 1307 for Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates except the Phthalate no.5-6,11 was conducted as per applicant requested only.

- NPR = Notice of proposed rulemaking
- %, w/w = Percentage weight by weight
- LOD = Limit of Detection
- LOQ = Limit of Quantitation
- ND = Not detected (Less than LOD)
- ▲ = Tested items are not included in the TISI Accreditation

Tested components:

| | | |
|-------------------------------------|-------|----------------|
| (11) = LIGHT ORANGE COATING ON WOOD | Refer | BKKH19009836 |
| (12) = BLUE COATING ON WOOD | Refer | BKKH19008028S1 |
| (13) = LIGHT YELLOW COATING ON WOOD | Refer | BKKH19009836 |



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH19009596S2

Test conducted:

8 Phthalate content test[▲]

By solvent extraction and Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

| | <u>Result</u> | | | | | <u>LOD</u> | <u>LOQ</u> | <u>Limit</u> |
|-----------------------------------|-----------------|-----|-----|-----|-----|-----------------|-----------------|-----------------|
| | <u>(%, w/w)</u> | | | | | <u>(%, w/w)</u> | <u>(%, w/w)</u> | <u>(%, w/w)</u> |
| | (1) | (2) | (3) | (4) | (5) | | | |
| Dibutyl Phthalate (DBP) | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 |
| Di(2-ethylhexyl) phthalate (DEHP) | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 |
| Benzyl butyl Phthalate (BBP) | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 |
| Di-iso-nonyl Phthalate (DINP) | ND | ND | ND | ND | ND | 0.0015 | 0.0090 | 0.1 |
| Diocetyl Phthalate (DNOP) | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 |
| Di-iso-decyl Phthalate (DIDP) | ND | ND | ND | ND | ND | 0.0015 | 0.0090 | 0.1 |
| Di-n-hexyl Phthalate (DnHP) | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 |

Remark : %, w/w = Percentage weight by weight
 LOD = Limit of Detection
 LOQ = Limit of Quantitation
 ND = Not detected (Less than LOD)
 ▲ = Tested items are not included in the TISI Accreditation

Note : The above limit was quoted according to the California Proposition 65

Tested components:

| | | | |
|-------|-------------------------|-------|----------------|
| (1) = | WHITE COATING ON WOOD | Refer | BKKH19007793S1 |
| (2) = | LACQUER COATING ON WOOD | Refer | BKKH19007792S1 |
| (3) = | RED COATING ON WOOD | Refer | BKKH19007790S1 |
| (4) = | BROWN COATING ON WOOD | Refer | BKKH19007792S1 |
| (5) = | BROWN PLASTIC JOINT | Refer | BKKH19009590S1 |



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH19009596S2

Test conducted:

Phthalate content test[▲]

By solvent extraction and Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

| | <u>Result</u> | | | | | <u>LOD</u> | <u>LOQ</u> | <u>Limit</u> |
|-----------------------------------|-----------------|-----|-----|-----|------|-----------------|-----------------|-----------------|
| | <u>(%, w/w)</u> | | | | | <u>(%, w/w)</u> | <u>(%, w/w)</u> | <u>(%, w/w)</u> |
| | (6) | (7) | (8) | (9) | (10) | | | |
| Dibutyl Phthalate (DBP) | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 |
| Di(2-ethylhexyl) phthalate (DEHP) | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 |
| Benzyl butyl Phthalate (BBP) | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 |
| Di-iso-nonyl Phthalate (DINP) | ND | ND | ND | ND | ND | 0.0015 | 0.0090 | 0.1 |
| Diocetyl Phthalate (DNOP) | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 |
| Di-iso-decyl Phthalate (DIDP) | ND | ND | ND | ND | ND | 0.0015 | 0.0090 | 0.1 |
| Di-n-hexyl Phthalate (DnHP) | ND | ND | ND | ND | ND | 0.0015 | 0.0030 | 0.1 |

Remark : %, w/w = Percentage weight by weight
 LOD = Limit of Detection
 LOQ = Limit of Quantitation
 ND = Not detected (Less than LOD)
 ▲ = Tested items are not included in the TISI Accreditation

Note : The above limit was quoted according to the California Proposition 65

Tested components:

| | | | |
|--------|------------------------|-------|----------------|
| (6) = | YELLOW COATING ON WOOD | Refer | BKKH19007790S1 |
| (7) = | WHITE COATING ON WOOD | Refer | BKKH19007793S1 |
| (8) = | BLACK COATING ON WOOD | Refer | BKKH19007793S1 |
| (9) = | BROWN COATING ON WOOD | Refer | BKKH19007791S1 |
| (10) = | PINK COATING ON WOOD | Refer | BKKH19007790S1 |



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH19009596S2

Test conducted:

Phthalate content test[▲]

By solvent extraction and Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

| | <u>Result</u> | | | <u>LOD</u> | <u>LOQ</u> | <u>Limit</u> |
|-----------------------------------|-----------------|------|------|-----------------|-----------------|-----------------|
| | <u>(%, w/w)</u> | | | <u>(%, w/w)</u> | <u>(%, w/w)</u> | <u>(%, w/w)</u> |
| | (11) | (12) | (13) | | | |
| Dibutyl Phthalate (DBP) | ND | ND | ND | 0.0015 | 0.0030 | 0.1 |
| Di(2-ethylhexyl) phthalate (DEHP) | ND | ND | ND | 0.0015 | 0.0030 | 0.1 |
| Benzyl butyl Phthalate (BBP) | ND | ND | ND | 0.0015 | 0.0030 | 0.1 |
| Di-iso-nonyl Phthalate (DINP) | ND | ND | ND | 0.0015 | 0.0090 | 0.1 |
| Diocetyl Phthalate (DNOP) | ND | ND | ND | 0.0015 | 0.0030 | 0.1 |
| Di-iso-decyl Phthalate (DIDP) | ND | ND | ND | 0.0015 | 0.0090 | 0.1 |
| Di-n-hexyl Phthalate (DnHP) | ND | ND | ND | 0.0015 | 0.0030 | 0.1 |

Remark : %, w/w = Percentage weight by weight
 LOD = Limit of Detection
 LOQ = Limit of Quantitation
 ND = Not detected (Less than LOD)
 ▲ = Tested items are not included in the TISI Accreditation

Note : The above limit was quoted according to the California Proposition 65

Tested components:

| | | | |
|--------|------------------------------|-------|----------------|
| (11) = | LIGHT ORANGE COATING ON WOOD | Refer | BKKH19009836 |
| (12) = | BLUE COATING ON WOOD | Refer | BKKH19008028S1 |
| (13) = | LIGHT YELLOW COATING ON WOOD | Refer | BKKH19009836 |



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH19009596S2

Test conducted:

9 Total Lead (Pb) Content[▲]

As per Illinois Lead poisoning prevention act 410 ILCS 45 section 6 (public act 095-1019), acid digestion method was used and total Lead content was determined by Inductively Couple Plasma Optical Emission Spectrometry.

I Surface coating material

| <u>Tested component</u> | <u>Result</u> mg/kg | <u>LOD</u> mg/kg | <u>LOQ</u> mg/kg | <u>Limit</u> mg/kg |
|-------------------------|------------------------|---------------------|---------------------|-----------------------|
| (1) | ND | 2 | 13 | 90 |
| (2) | ND | 2 | 13 | 90 |
| (3) | ND | 2 | 13 | 90 |
| (4) | ND | 2 | 13 | 90 |
| (5) | ND | 2 | 13 | 90 |
| (6) | ND | 2 | 13 | 90 |
| (7) | ND | 2 | 13 | 90 |
| (8) | ND | 2 | 13 | 90 |
| (9) | ND | 2 | 13 | 90 |
| (10) | <13 | 2 | 13 | 90 |
| (11) | ND | 2 | 13 | 90 |
| (12) | ND | 2 | 13 | 90 |

Remark: < = Less than
mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
LOD = Limit of Detection
LOQ = Limit of Quantitation
ND = Not detected (Less than LOD)
▲ = Tested items are not included in the TISI Accreditation

Requirement: According to Illinois Lead poisoning prevention act 410 ILCS 45 section 6 (public act 095-019), appropriate warning statement is required when the Lead content of the submitted sample is more than 40 ppm but less than 90 ppm for surface coatings and less than 100 ppm for substrates by total weight or a lower standard for Lead content as may be established by federal or state law or regulation.



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.



Number: BKKH19009596S2

Test conducted:

Tested components:

- (1) = WHITE COATING ON WOOD
- (2) = LACQUER COATING ON WOOD
- (3) = RED COATING ON WOOD
- (4) = BROWN COATING ON WOOD
- (5) = YELLOW COATING ON WOOD
- (6) = WHITE COATING ON WOOD
- (7) = BLACK COATING ON WOOD
- (8) = BROWN COATING ON WOOD
- (9) = PINK COATING ON WOOD
- (10) = LIGHT ORANGE COATING ON WOOD
- (11) = BLUE COATING ON WOOD
- (12) = LIGHT YELLOW COATING ON WOOD

- Refer BKKH19007793S1
- Refer BKKH19007792S1
- Refer BKKH19007790S1
- Refer BKKH19007792S1
- Refer BKKH19007790S1
- Refer BKKH19007793S1
- Refer BKKH19007793S1
- Refer BKKH19007791S1
- Refer BKKH19007790S1
- Refer BKKH19009836
- Refer BKKH19008028S1
- Refer BKKH19009836



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH19009596S2

Test conducted:

II Non-surface coating material (substrate)

| <u>Tested component</u> | <u>Result</u> | <u>LOD</u> | <u>LOQ</u> | <u>Limit</u> |
|-------------------------|---------------|--------------|--------------|--------------|
| | <u>mg/kg</u> | <u>mg/kg</u> | <u>mg/kg</u> | <u>mg/kg</u> |
| (13) | ND | 1 | 13 | 100 |

Remark:

mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
 LOD = Limit of Detection
 LOQ = Limit of Quantitation
 ND = Not detected (Less than LOD)

Requirement: According to Illinois Lead poisoning prevention act 410 ILCS 45 section 6 (public act 095-019), appropriate warning statement is required when the Lead content of the submitted sample is more than 40 ppm but less than 90 ppm for surface coatings and less than 100 ppm for substrates by total weight or a lower standard for Lead content as may be established by federal or state law or regulation.

Tested components:

(13) = BROWN PLASTIC JOINT

Refer BKKH19009590S1

Note: LOD and LOQ value in this test report were effective since October, 2014

*****END*****/KS/NK

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our standard Terms and Conditions which can be obtained at our website: <http://www.intertek.com/terms/>. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. This report is made solely on the basis of your instructions and / or information and materials supplied by you and provide no warranty on the tested sample(s) be truly representative of the sample source. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. This report does not discharge or release you from your legal obligations and duties to any other person. You are the only one authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk. This report shall not be reproduced, except in full.

