

TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH18013313

Applicant: PLAN CREATIONS CO., LTD.
8 MOO 8, TRANG-PALIAN RD.,
YANTAKAO, TRANG, THAILAND 92140
ATTN: K.NARONG, K.SUPAPORN

Date: Dec 14, 2018

Sample description:

Quantity of sample:	One (1) set
Sample description:	Wooden toy
Date sample received:	October 04, 2018
Date information received:	December 03, 2018

Client Information:

One (1) set of submitted sample said to be FINDING AN ELEPHANT

Item Name: FINDING AN ELEPHANT
Item Number: 4624



Test conducted:

As requested by the applicant, for details please refer to attached page(s)

To be continued

For and on behalf of :
Intertek Testing Services (Thailand) Ltd.,
Hardlines Laboratory

Ladtaka Wongwiboonporn

Ladtaka Wongwiboonporn
Laboratory Manager
Hardlines Department

TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH18013313

Conclusion:

Tested samples

Submitted sample

Standard

U.S. ASTM F963-17 for Physical and mechanical tests

Result

Pass

U.S. ASTM F963-17 for Flammability test of materials
other than textile materials

Pass

U.S. ASTM F963-16 for Heavy elements Test

Pass

Standard - U.S. CFR title 16

(CPSC regulations)

Pass

Part 1303 total Lead content

16 CFR Part 1610

Pass

Flammability test

Standard

U.S. Consumer product safety improvement
Act 2008(H.R. 4040) Title I, Section 101
For total lead content in surface coating

Pass

U.S. Consumer product safety improvement
Act 2008(H.R. 4040) Title I, Section 101

Pass

For total lead content in non-surface coating material (substrate)

US 16 CFR Part 1307 for Prohibition of Children's Toys
and Child Care Articles Containing Specified Phthalates

Pass

Phthalate Content Requirement base
on the California Proposition 65

Pass

Illinois Lead Poisoning Prevention

Pass

Act 410 ILCS 45 section 6 (public act 095-1019)

Remark: As requested by the applicant, the test was conducted only on components listed in this report.
Other components were not tested.

TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH18013313

Remark:

The chemical test results was not conducted on the below components of samples. Applicant claimed the components were tested on our previous test report.

<u>Components</u>	<u>Report No.</u>	<u>Date</u>
<u>ASTM F963-16: Heavy metal</u>		
LIGHT GRAY COATING ON WOOD	BKKH17014794	Dec 06, 2017
ORANGE COATING ON WOOD	BKKH18001632	Feb 12, 2018
PURPLE COATING ON WOOD	BKKH18001632	Feb 12, 2018
WHITE COATING ON WOOD	BKKH18008771	Jul 12, 2018
BROWN COATING ON WOOD	BKKH18008771	Jul 12, 2018
LACQUER COATING ON WOOD	BKKH18008771	Jul 12, 2018
PINK COATING ON WOOD	BKKH18009874	Aug 01, 2018
WHITE FABRIC WITH BROWN PRINT	BKKH18009385S1	Aug 01, 2018
CREAM COTTON CORD	BKKH18009385S1	Aug 01, 2018
<u>Lead in surface coating</u>		
LIGHT GRAY COATING ON WOOD	BKKH17014794	Dec 06, 2017
ORANGE COATING ON WOOD	BKKH18001632	Feb 12, 2018
PURPLE COATING ON WOOD	BKKH18001632	Feb 12, 2018
WHITE COATING ON WOOD	BKKH18008771	Jul 12, 2018
BROWN COATING ON WOOD	BKKH18008771	Jul 12, 2018
LACQUER COATING ON WOOD	BKKH18008771	Jul 12, 2018
PINK COATING ON WOOD	BKKH18009874	Aug 01, 2018
<u>Lead in substrate</u>		
WHITE FABRIC WITH BROWN PRINT	BKKH18009385S1	Aug 01, 2018
CREAM COTTON CORD	BKKH18009385S1	Aug 01, 2018
<u>Phthalate content</u>		
LIGHT GRAY COATING ON WOOD	BKKH17014794	Dec 06, 2017
ORANGE COATING ON WOOD	BKKH18001632	Feb 12, 2018
PURPLE COATING ON WOOD	BKKH18001632	Feb 12, 2018
WHITE COATING ON WOOD	BKKH18008771	Jul 12, 2018
BROWN COATING ON WOOD	BKKH18008771	Jul 12, 2018
LACQUER COATING ON WOOD	BKKH18008771	Jul 12, 2018
PINK COATING ON WOOD	BKKH18009874	Aug 01, 2018



TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH18013313

Test conducted:

1 Physical And Mechanical Tests▲

Test Standard : ASTM Standard Consumer Safety Specification for Toy Safety F963-17.

Age group for testing : For age over 3 years

The submitted samples were undergone the use and abuse tests in accordance with the Federal Hazardous Substances Act (FHSA), Title 16, Code of Federal Regulations : -

Test	FHSA	Parameter
Drop test	Section 1500.53(b)	4 x 3.0 ft
Torque test	Section 1500.53(e)	4 in-lbf
Tension test	Section 1500.53(f)	15 lbf

Clause	Testing items	Assessment
4.1	Material quality	P
4.5	Sound-producing toys	NA
4.6.1	Toys intended for children under 36 months (small objects)	NA
4.6.2	Mouth-actuated toys	NA
4.6.3	Toys and games for 36 months to 72 months (small part warning)	P
4.7	Accessible edges	NA
4.8	Projections	NA
4.9	Accessible points	P
4.10	Wires or rods	NA
4.11	Nails and fasteners	NA
4.12	Plastic film	NA
4.13	Folding mechanisms and hinges	NA
4.14	Cords, straps and elastics	NA
4.15	Stability and over-load requirements	NA
4.16	Confined spaces	NA
4.17	Wheels, tires and axles	NA
4.18	Holes, clearance, and accessibility of mechanisms	NA
4.19	Simulated protective devices	NA
4.20	Pacifiers	NA
4.21	Projectile toys	NA
4.22	Teethers and teething toys	NA

TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH18013313

Test conducted:

Clause	Testing items	Assessment
4.23	Rattles	NA
4.24	Squeeze toys	NA
4.25	Battery-operated toys	NA
4.26	Toys intended to be attached to a crib or playpen	NA
4.27	Stuffed and beanbag-type toys	NA
4.28	Stroller and carriage toys	NA
4.29	Art materials	NA
4.30	Toy gun marking	NA
4.31	Balloons	NA
4.32	Certain toys with nearly spherical ends	NA
4.33	Marbles	NA
4.34	Balls	NA
4.35	Pompoms	NA
4.36	Hemispheric-shaped objects	NA
4.37	Yoyo elastic tether toys	NA
4.38	Magnets	NA
4.39	Jaw entrapment in handles and steering wheels	NA
4.40	Expanding materials	NA
4.41	Toy chests	NA
5	Labelling requirement	P
6	Instructional literature	P
7	Producer's markings - name of producer (toy and package) - address (package)	Yes Yes

Remark : P = Pass NA = Not applicable

▲ = Tested items are not included in the TISI Accreditation

The submitted samples were undergone the tests in accordance with clause 8.5 through clause 8.17 and 8.19 through 8.26 on normal use, abuse and specific tests for different types of toys whichever is applicable.

Testing period : October 04, 2018 to October 11, 2018

2 Flammability Test▲

Test Standard : Clause 4.2 of the ASTM Standard Consumer Safety Specification for Toy Safety F963-17.

Results : Did not ignite

▲ = Tested items are not included in the TISI Accreditation

Testing period : October 04, 2018 to October 11, 2018

TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH18013313

Test conducted:

3 Flammability Test (US CPSC 16 CFR Part 1610)[▲]

x Plain surface

o Raised surface

Burn direction:		x length o width		Burn direction:		x length o width	
Prelim Raised surface:				Prelim Raised surface:			
length : DNI				length : DNI			
width : DNI				width : DNI			
<u>Original</u> <u>(seconds)</u>				<u>After one drycleaning/laundry</u> <u>(seconds)</u>			<u>Requirement</u>
1	DNI			1	DNI		Class 1
2	DNI			2	DNI		
3	DNI			3	DNI		
4	DNI			4	DNI		
5	DNI			5	DNI		

Classification:

x class 1,

Normal flammability

o class 2,

Intermediate flammability, raised surface

o class 3,

Rapid and intense burning

Explanation of flammability results:

IBE Ignited but extinguished, the asterisk () denotes a burn that goes under the cord without breaking the cord.

DNI Did not ignite.

IBE Ignited but extinguished.

0.0 BB Actual time of burn from ignition until the flame severs the cord directly above the specimen (releasing the weight which in turn stops the timer) will give a numerical time in 0.0 seconds

*0.0SFBB Time in seconds, surface flash base burn possibly starting at the point of impingement.

Poi The asterisk is accompanied by the following: "unable to make absolute determination as to source of base burns." burning. It does not qualify as a base burn under the current interpretation of cfr 1610.

0.0SF Only Time in seconds, surface flash only. No damage to the base fabric.

0.0 SFBB Time in seconds, surface flash base burn. Base starts burning at points other than the point of impingement.

SF pw Surface flash, part way. No time shown because the surface flash did not reach the cord.

SF uc Surface flash under the cord, but does not break the cord.

SF poi Surface flash, at point of impingement only (equivalent to "did not ignite" for plain surface).

Plain surface fabric with an average burn time less than 4.0 seconds as class 3 flammability verse the 16 CFR 1610 standard of 3.5 seconds.

▲ = Tested items are not included in the TISI Accreditation

Test component: Cream fabric

Testing period : October 22, 2018 to October 25, 2018



TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH18013313

Test conducted:

4 Heavy Elements Analysis

As per clause 4.3.5.1(2) of the ASTM Standard Consumer Safety Specification on Toy Safety F963-16, acid extraction method was used and heavy elements migration content were determined by ICP-OES analysis.

	(1)	(2)	<u>Result</u> <u>mg/kg</u>	(4)	(5)	<u>LOD</u> <u>mg/kg</u>	<u>LOQ</u> <u>mg/kg</u>	<u>Limit mg/kg</u>
Sol. Barium (Ba)	10	216	99	10	572	1	5	1000
Sol. Lead (Pb)	ND	ND	ND	ND	ND	1	5	90
Sol. Cadmium (Cd)	ND	ND	ND	ND	ND	1	5	75
Sol. Antimony (Sb)	ND	ND	ND	ND	ND	2	5	60
Sol. Selenium (Se)	ND	ND	ND	ND	ND	1	5	500
Sol. Chromium (Cr)	ND	ND	ND	ND	ND	2	5	60
Sol. Mercury (Hg)	ND	ND	ND	ND	ND	1	5	60
Sol. Arsenic (As)	ND	ND	ND	ND	ND	2	5	25

Remark: Sol. = Soluble
mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
LOD = Limit of Detection LOQ = Limit of Quantitation
ND = Not detected (Less than LOD)

Tested components:

(1) =	LIGHT GRAY COATING ON WOOD	Refer	BKKH17014794
(2) =	ORANGE COATING ON WOOD	Refer	BKKH18001632
(3) =	PURPLE COATING ON WOOD	Refer	BKKH18001632
(4) =	WHITE COATING ON WOOD	Refer	BKKH18008771
(5) =	BROWN COATING ON WOOD	Refer	BKKH18008771

Note: The results of soluble toxic elements were adjusted by subtracting the analytical correction factor.

TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH18013313

Test conducted:

Heavy Elements Analysis

As per clause 4.3.5.1(2) of the ASTM Standard Consumer Safety Specification on Toy Safety F963-16, acid extraction method was used and heavy elements migration content were determined by ICP-OES analysis.

	<u>Result</u> <u>mg/kg</u>		<u>LOD</u> <u>mg/kg</u>	<u>LOQ</u> <u>mg/kg</u>	<u>Limit mg/kg</u>
	(6)	(7)			
Sol. Barium (Ba)	<5	49	1	5	1000
Sol. Lead (Pb)	ND	<5	1	5	90
Sol. Cadmium (Cd)	ND	ND	1	5	75
Sol. Antimony (Sb)	ND	ND	2	5	60
Sol. Selenium (Se)	ND	ND	1	5	500
Sol. Chromium (Cr)	ND	ND	2	5	60
Sol. Mercury (Hg)	ND	ND	1	5	60
Sol. Arsenic (As)	ND	ND	2	5	25

Remark: Sol. = Soluble
mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
LOD = Limit of Detection LOQ = Limit of Quantitation
ND = Not detected (Less than LOD) < = Less than

Tested components:

(6) = LACQUER COATING ON WOOD Refer BKKH18008771
(7) = PINK COATING ON WOOD Refer BKKH18009874

Note: The results of soluble toxic elements were adjusted by subtracting the analytical correction factor.

TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH18013313

Test conducted:

Heavy Elements Analysis

As per clause 4.3.5.2(2)(b) of the ASTM Standard Consumer Safety Specification on Toy Safety F963-16, acid extraction method was used and heavy elements migration content were determined by ICP-OES analysis.

	<u>Result</u> <u>mg/kg</u>		<u>LOD</u> <u>mg/kg</u>	<u>LOQ</u> <u>mg/kg</u>	<u>Limit mg/kg</u>
	(8)	(9)			
Sol. Barium (Ba)	ND	ND	1	5	1000
Sol. Lead (Pb)	ND	ND	1	5	90
Sol. Cadmium (Cd)	ND	ND	1	5	75
Sol. Antimony (Sb)	<5	<5	2	5	60
Sol. Selenium (Se)	ND	ND	1	5	500
Sol. Chromium (Cr)	ND	ND	2	5	60
Sol. Mercury (Hg)	ND	ND	1	5	60
Sol. Arsenic (As)	ND	ND	2	5	25

Remark: Sol. = Soluble
mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
LOD = Limit of Detection LOQ = Limit of Quantitation
ND = Not detected (Less than LOD) < = Less than

Tested components:

(8) =	WHITE FABRIC WITH BROWN PRINT	Refer	BKKH18009385S1
(9) =	CREAM COTTON CORD	Refer	BKKH18009385S1

Note: The results of soluble toxic elements were adjusted by subtracting the analytical correction factor.

TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH18013313

Test conducted:

Total Lead (Pb) Content

As per clause 4.3.5.1(1) of the ASTM Standard Consumer Safety Specification on Toy Safety F963-16, test method CPSC-CH-E1003-09.1:2011 was used and total Lead content was determined by ICP-OES analysis.

(I) Surface coating

Tested Component	Result mg/kg	LOD (mg/kg)	LOQ (mg/kg)	Limit (mg/kg)
(1)	ND	2	13	90
(2)	ND	2	13	90
(3)	ND	2	13	90
(4)	<13	2	13	90
(5)	ND	2	13	90
(6)	ND	2	13	90
(7)	ND	2	13	90

Remark: mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
 LOD = Limit of Detection
 ND = Not detected (Less than LOD)
 LOQ = Limit of Quantitation
 < = Less than

Tested components:

(1) =	LIGHT GRAY COATING ON WOOD	Refer	BKKH17014794
(2) =	ORANGE COATING ON WOOD	Refer	BKKH18001632
(3) =	PURPLE COATING ON WOOD	Refer	BKKH18001632
(4) =	WHITE COATING ON WOOD	Refer	BKKH18008771
(5) =	BROWN COATING ON WOOD	Refer	BKKH18008771
(6) =	LACQUER COATING ON WOOD	Refer	BKKH18008771
(7) =	PINK COATING ON WOOD	Refer	BKKH18009874

TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH18013313

Test conducted:

Total Lead (Pb) Content

As per clause 4.3.5.2(2)(a) of the ASTM Standard Consumer Safety Specification on Toy Safety F963-16, test method CPSC-CH-E1001-08.3:2012, CPSC-CH-E1002-08.3:2012 were used and total Lead content was determined by ICP-OES analysis.

(II) Non-surface coating

<u>Tested Component</u>	<u>Result</u> <u>mg/kg</u>	<u>LOD</u> <u>(mg/kg)</u>	<u>LOQ</u> <u>(mg/kg)</u>	<u>Limit</u> <u>(mg/kg)</u>
(8)	ND	1	13	100
(9)	ND	1	13	100

Remark: mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
LOD = Limit of Detection LOQ = Limit of Quantitation
ND = Not detected (Less than LOD) < = Less than

Tested components:

(8) = WHITE FABRIC WITH BROWN PRINT

Refer BKKH18009385S1

(9) = CREAM COTTON CORD

Refer BKKH18009385S1

The report shall not be reproduced without written approval from Intertek.

The results relate only to the item tested.

Test conducted:

As per U.S. Code of Federal Regulations title 16 Part 1303. Acid digestion method was used and total Lead content was determined by Inductively Couple Plasma Optical Emission Spectrometry.²

<u>Tested component</u>	<u>Result %</u>	<u>LOD %</u>	<u>LOQ %</u>	<u>Limit %</u>
(1)	ND	0.0002	0.0013	0.0090
(2)	ND	0.0002	0.0013	0.0090
(3)	ND	0.0002	0.0013	0.0090
(4)	<0.0013	0.0002	0.0013	0.0090
(5)	ND	0.0002	0.0013	0.0090
(6)	ND	0.0002	0.0013	0.0090
(7)	ND	0.0002	0.0013	0.0090

Remark: % = percentage < = Less than
LOD = Limit of Detection LOQ = Limit of Quantitation
ND = Not detected (Less than LOD)
▲ = Tested items are not included in the TISI Accreditation

Tested components:

(1) =	LIGHT GRAY COATING ON WOOD	Refer	BKKH17014794
(2) =	ORANGE COATING ON WOOD	Refer	BKKH18001632
(3) =	PURPLE COATING ON WOOD	Refer	BKKH18001632
(4) =	WHITE COATING ON WOOD	Refer	BKKH18008771
(5) =	BROWN COATING ON WOOD	Refer	BKKH18008771
(6) =	LACQUER COATING ON WOOD	Refer	BKKH18008771
(7) =	PINK COATING ON WOOD	Refer	BKKH18009874



TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH18013313

Test conducted:

- 6 Total lead (Pb) content in surface coating
As per U.S. Consumer Product Safety Improvement Act of 2008 (H.R. 4040), Title I, Section 101 for children's products containing Lead, CPSC-CH-E1003-09.1:2011 method was used and total Lead content was determined by Inductively Couple Plasma Optical Emission Spectrometry.

<u>Tested component</u>	<u>Result</u> <u>mg/kg</u>	<u>LOD</u> <u>mg/kg</u>	<u>LOQ</u> <u>mg/kg</u>	<u>Limit mg/kg</u>
(1)	ND	2	13	90
(2)	ND	2	13	90
(3)	ND	2	13	90
(4)	<13	2	13	90
(5)	ND	2	13	90
(6)	ND	2	13	90
(7)	ND	2	13	90

Remark: mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
LOD = Limit of Detection LOQ = Limit of Quantitation
ND = Not detected (Less than LOD) < = Less than

Tested components:

(1) =	LIGHT GRAY COATING ON WOOD	Refer	BKKH17014794
(2) =	ORANGE COATING ON WOOD	Refer	BKKH18001632
(3) =	PURPLE COATING ON WOOD	Refer	BKKH18001632
(4) =	WHITE COATING ON WOOD	Refer	BKKH18008771
(5) =	BROWN COATING ON WOOD	Refer	BKKH18008771
(6) =	LACQUER COATING ON WOOD	Refer	BKKH18008771
(7) =	PINK COATING ON WOOD	Refer	BKKH18009874

TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH18013313

Test conducted:

7 Total lead (Pb) content in substrate material- non-metal children's product

As per U.S. Consumer product safety improvement Act of 2008 (H.R. 4040), Title I, Section 101 for children's products containing lead, CPSC-CH-E1002-08.3:2012 method was used and total lead content was determined by Inductively Couple Plasma Optical Emission Spectrometry.☐


<u>Tested component</u>	<u>Result</u> <u>mg/kg</u>	<u>LOD</u> <u>mg/kg</u>	<u>LOQ</u> <u>mg/kg</u>	<u>Limit mg/kg</u>
(1)	ND	1	13	100
(2)	ND	1	13	100

Remark: mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
 LOD = Limit of Detection LOD = Limit of Quantitation
 ND = Not detected (Less than LOD)

Tested components:

- (1) = WHITE FABRIC WITH BROWN PRINT
 (2) = CREAM COTTON CORD

Refer BKKH18009385S1
 Refer BKKH18009385S1



TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH18013313

Test conducted:

8 Phthalate content

As per CPSC-CH-C1001-09.3:2010 and U.S. Consumer Product Safety Improvement Act 2008 (H.R. 4040), Title I, Section 108 requirement on Phthalates, solvent extraction method was used and Phthalate content was determined by Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.☐

	<u>Result</u> (%, w/w)					<u>LOD</u> (%, w/w)	<u>LOQ</u> (%, w/w)	<u>(16CFR1307)</u> Limit (%, w/w)	<u>NPR</u> (%, w/w)
	(1)	(2)	(3)	(4)	(5)				
Dibutyl Phthalate (DBP)	ND	ND	ND	ND	ND	0.0015	0.0030	0.1	0.1
Di(2-ethylhexyl) phthalate (DEHP)	ND	ND	ND	ND	ND	0.0015	0.0030	0.1	0.1
Benzyl butyl Phthalate (BBP)	ND	ND	ND	ND	ND	0.0015	0.0030	0.1	0.1
Di-iso-nonyl Phthalate (DINP)	ND	ND	ND	ND	ND	0.0015	0.0090	0.1	0.1
Di-n-octyl Phthalate (DNOP)	ND	ND	ND	ND	ND	0.0015	0.0030	--	--
Di-iso-decyl Phthalate (DIDP)	ND	ND	ND	ND	ND	0.0015	0.0090	--	--
Di-isobutyl phthalate (DIBP)▲	ND	ND	ND	ND	ND	0.0015	0.0030	0.1	0.1
Di-n-pentyl phthalate (DPENP)▲	ND	ND	ND	ND	ND	0.0015	0.0030	0.1	0.1
Di-n-hexyl phthalate (DHEXP)▲	ND	ND	ND	ND	ND	0.0015	0.0030	0.1	0.1
Di-cyclohexyl phthalate (DCHP)▲	ND	ND	ND	ND	ND	0.0015	0.0030	0.1	0.1
Diisooctyl phthalate (DIOP)▲	ND	ND	ND	ND	ND	0.0015	0.0090	--	--

Remark : The above limit was quoted according to US 16 CFR Part 1307 for Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates except the Phthalate no.5-6,11 was conducted as per applicant requested only.

NPR = Notice of proposed rulemaking

%, w/w = Percentage weight by weight

LOD = Limit of Detection

LOQ = Limit of Quantitation

ND = Not detected (Less than LOD)

▲ = Tested items are not included in the TISI Accreditation

Tested components:

(1) =	LIGHT GRAY COATING ON WOOD	Refer	BKKH17014794
(2) =	ORANGE COATING ON WOOD	Refer	BKKH18001632
(3) =	PURPLE COATING ON WOOD	Refer	BKKH18001632
(4) =	WHITE COATING ON WOOD	Refer	BKKH18008771
(5) =	BROWN COATING ON WOOD	Refer	BKKH18008771

TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH18013313

Test conducted:

Phthalate content

As per CPSC-CH-C1001-09.3:2010 and U.S. Consumer Product Safety Improvement Act 2008 (H.R. 4040), Title I, Section 108 requirement on Phthalates, solvent extraction method was used and Phthalate content was determined by Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.☐

	<u>Result</u> <u>(%, w/w)</u>		<u>LOD</u> <u>(%, w/w)</u>	<u>LOQ</u> <u>(%, w/w)</u>	<u>(16CFR1307)</u> <u>Limit (%, w/w)</u>	<u>NPR</u> <u>(%, w/w)</u>
	(6)	(7)				
Dibutyl Phthalate (DBP)	ND	ND	0.0015	0.0030	0.1	0.1
Di(2-ethylhexyl) phthalate (DEHP)	ND	ND	0.0015	0.0030	0.1	0.1
Benzyl butyl Phthalate (BBP)	ND	ND	0.0015	0.0030	0.1	0.1
Di-iso-nonyl Phthalate (DINP)	ND	ND	0.0015	0.0090	0.1	0.1
Di-n-octyl Phthalate (DNOP)	ND	ND	0.0015	0.0030	--	--
Di-iso-decyl Phthalate (DIDP)	ND	ND	0.0015	0.0090	--	--
Di-isobutyl phthalate (DIBP)▲	ND	ND	0.0015	0.0030	0.1	0.1
Di-n-pentyl phthalate (DPENP)▲	ND	ND	0.0015	0.0030	0.1	0.1
Di-n-hexyl phthalate (DHEXP)▲	ND	ND	0.0015	0.0030	0.1	0.1
Di-cyclohexyl phthalate (DCHP)▲	ND	ND	0.0015	0.0030	0.1	0.1
Diisooctyl phthalate (DIOP)▲	ND	ND	0.0015	0.0090	--	--

Remark : The above limit was quoted according to US 16 CFR Part 1307 for Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates except the Phthalate no.5-6,11 was conducted as per applicant requested only.

NPR = Notice of proposed rulemaking

%, w/w = Percentage weight by weight

LOD = Limit of Detection

LOQ = Limit of Quantitation

ND = Not detected (Less than LOD)

▲ = Tested items are not included in the TISI Accreditation

Tested components:

(6) = LACQUER COATING ON WOOD

Refer BKKH18008771

(7) = PINK COATING ON WOOD

Refer BKKH18009874



TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH18013313

Test conducted:

9 Phthalate content test▲

By solvent extraction and Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

	<u>Result</u>					<u>LOD</u>	<u>LOQ</u>	<u>Limit</u>
	<u>(%, w/w)</u>					<u>(%, w/w)</u>	<u>(%, w/w)</u>	<u>(%, w/w)</u>
	(1)	(2)	(3)	(4)	(5)			
Dibutyl Phthalate (DBP)	ND	ND	ND	ND	ND	0.0015	0.0030	0.1
Di(2-ethylhexyl) phthalate (DEHP)	ND	ND	ND	ND	ND	0.0015	0.0030	0.1
Benzyl butyl Phthalate (BBP)	ND	ND	ND	ND	ND	0.0015	0.0030	0.1
Di-iso-nonyl Phthalate (DINP)	ND	ND	ND	ND	ND	0.0015	0.0090	0.1
Di-octyl Phthalate (DNOP)	ND	ND	ND	ND	ND	0.0015	0.0030	0.1
Di-iso-decyl Phthalate (DIDP)	ND	ND	ND	ND	ND	0.0015	0.0090	0.1
Di-n-hexyl Phthalate (DnHP)	ND	ND	ND	ND	ND	0.0015	0.0030	0.1

Remark : %, w/w = Percentage weight by weight

LOD = Limit of Detection

LOQ = Limit of Quantitation

ND = Not detected (Less than LOD)

▲ = Tested items are not included in the TISI Accreditation

Note : The above limit was quoted according to the California Proposition 65

Tested components:

(1) =	LIGHT GRAY COATING ON WOOD	Refer	BKKH17014794
(2) =	ORANGE COATING ON WOOD	Refer	BKKH18001632
(3) =	PURPLE COATING ON WOOD	Refer	BKKH18001632
(4) =	WHITE COATING ON WOOD	Refer	BKKH18008771
(5) =	BROWN COATING ON WOOD	Refer	BKKH18008771

TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH18013313

Test conducted:

Phthalate content test[▲]

By solvent extraction and Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

	<u>Result</u> <u>(%, w/w)</u>		<u>LOD</u> <u>(%, w/w)</u>	<u>LOQ</u> <u>(%, w/w)</u>	<u>Limit</u> <u>(%, w/w)</u>
	(6)	(7)			
Dibutyl Phthalate (DBP)	ND	ND	0.0015	0.0030	0.1
Di(2-ethylhexyl) phthalate (DEHP)	ND	ND	0.0015	0.0030	0.1
Benzyl butyl Phthalate (BBP)	ND	ND	0.0015	0.0030	0.1
Di-iso-nonyl Phthalate (DINP)	ND	ND	0.0015	0.0090	0.1
Diocetyl Phthalate (DNOP)	ND	ND	0.0015	0.0030	0.1
Di-iso-decyl Phthalate (DIDP)	ND	ND	0.0015	0.0090	0.1
Di-n-hexyl Phthalate (DnHP)	ND	ND	0.0015	0.0030	0.1

Remark : %, w/w = Percentage weight by weight

 LOD = Limit of Detection

 LOQ = Limit of Quantitation

 ND = Not detected (Less than LOD)

[▲] = Tested items are not included in the TISI Accreditation

Note : The above limit was quoted according to the California Proposition 65

Tested components:

(6) = LACQUER COATING ON WOOD

Refer BKKH18008771

(7) = PINK COATING ON WOOD

Refer BKKH18009874

TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH18013313

Test conducted:

10 Total Lead (Pb) Content[▲]

As per Illinois Lead poisoning prevention act 410 ILCS 45 section 6 (public act 095-1019), acid digestion method was used and total Lead content was determined by Inductively Couple Plasma Optical Emission Spectrometry.

I Surface coating material

<u>Tested component</u>	<u>Result</u> <u>mg/kg</u>	<u>LOD</u> <u>mg/kg</u>	<u>LOQ</u> <u>mg/kg</u>	<u>Limit</u> <u>mg/kg</u>
(1)	ND	2	13	90
(2)	ND	2	13	90
(3)	ND	2	13	90
(4)	<13	2	13	90
(5)	ND	2	13	90
(6)	ND	2	13	90
(7)	ND	2	13	90

Remark: < = Less than
mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
LOD = Limit of Detection
LOQ = Limit of Quantitation
ND = Not detected (Less than LOD)
▲ = Tested items are not included in the TISI Accreditation

Requirement: According to Illinois Lead poisoning prevention act 410 ILCS 45 section 6 (public act 095-019), appropriate warning statement is required when the Lead content of the submitted sample is more than 40 ppm but less than 90 ppm for surface coatings and less than 100 ppm for substrates by total weight or a lower standard for Lead content as may be established by federal or state law or regulation.

Tested components:

(1) =	LIGHT GRAY COATING ON WOOD	Refer	BKKH17014794
(2) =	ORANGE COATING ON WOOD	Refer	BKKH18001632
(3) =	PURPLE COATING ON WOOD	Refer	BKKH18001632
(4) =	WHITE COATING ON WOOD	Refer	BKKH18008771
(5) =	BROWN COATING ON WOOD	Refer	BKKH18008771
(6) =	LACQUER COATING ON WOOD	Refer	BKKH18008771
(7) =	PINK COATING ON WOOD	Refer	BKKH18009874

TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH18013313

Test conducted:

II Non-surface coating material (substrate)

<u>Tested component</u>	<u>Result</u>	<u>LOD</u>	<u>LOQ</u>	<u>Limit</u>
	<u>mg/kg</u>	<u>mg/kg</u>	<u>mg/kg</u>	<u>mg/kg</u>
(8)	ND	1	13	100
(9)	ND	1	13	100

Remark:

mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
LOD = Limit of Detection
LOQ = Limit of Quantitation
ND = Not detected (Less than LOD)

Requirement:

According to Illinois Lead poisoning prevention act 410 ILCS 45 section 6 (public act 095-019), appropriate warning statement is required when the Lead content of the submitted sample is more than 40 ppm but less than 90 ppm for surface coatings and less than 100 ppm for substrates by total weight or a lower standard for Lead content as may be established by federal or state law or regulation.

Tested components:

(8) =	WHITE FABRIC WITH BROWN PRINT	Refer	BKKH18009385S1
(9) =	CREAM COTTON CORD	Refer	BKKH18009385S1

Note: LOD and LOQ value in this test report were effective since October, 2014

*****END*****/KS/NK

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our standard Terms and Conditions which can be obtained at our website: <http://www.intertek.com/terms/>. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. This report is made solely on the basis of your instructions and / or information and materials supplied by you and provide no warranty on the tested sample(s) be truly representative of the sample source. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. This report does not discharge or release you from your legal obligations and duties to any other person. You are the only one authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk. This report shall not be reproduced, except in full.