

TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH20000456

Applicant: PLAN CREATIONS CO., LTD.
8 MOO 8, TRANG-PALIAN RD.,
YANTAKAO, TRANG, THAILAND 92140
ATTN: K.NARONG, K.RATCHADA

Issued Date: Feb 17, 2020

Sample description:

Quantity of sample:	One (1) set
Sample description:	Wooden toy
Date sample received:	January 15, 2020
Date information received:	February 13, 2020

Client Information:

One (1) set of submitted sample said to be STACKING TREE

Item Name: STACKING TREE
Item Number: 5149



Test conducted:

As requested by the applicant, for details please refer to attached page(s)

To be continued

For and on behalf of :
Intertek Testing Services (Thailand) Ltd.,
Hardlines Laboratory



Ladtaka Wongwiboonporn
Laboratory Manager
Hardlines Department

TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.



Number: BKKH20000456

Conclusion:

<u>Tested samples</u> Submitted sample	<u>Standard</u>	<u>Result</u>
	U.S. ASTM F963-17 for Physical and mechanical tests	Pass
	U.S. ASTM F963-17 for Flammability test of materials other than textile materials	Pass
	U.S. ASTM F963-17 for Heavy elements Test	Pass
	<u>Standard - U.S. CFR title 16</u> (CPSC regulations) Part 1303 total Lead content	Pass
	<u>Standard</u> U.S. Consumer product safety improvement Act 2008(H.R. 4040) Title I, Section 101 For total lead content in surface coating	Pass
	U.S. Consumer product safety improvement Act 2008(H.R. 4040) Title I, Section 101 For total lead content in non-surface coating material (substrate)	Pass
	US 16 CFR Part 1307 for Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates	Pass
	Phthalate Content Requirement base on the California Proposition 65	Pass
	Illinois Lead Poisoning Prevention Act 410 ILCS 45 section 6 (public act 095-1019)	Pass



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH20000456

Remark:

The chemical test results was not conducted on the below components of samples. Applicant claimed the components were tested on our previous test report.

<u>Components</u>	<u>Report No.</u>	<u>Date</u>
<u>ASTM F963-17: Heavy metal</u>		
LIGHT GREEN COATING ON WOOD	BKKH19008312S1	Jul 15, 2019
YELLOW COATING ON WOOD	BKKH19009836	Aug 15, 2019
LIGHT GREEN COATING ON WOOD	BKKH19008312S1	Jul 15, 2019
DARK GREEN COATING ON WOOD	BKKH20000806	Feb 12, 2020
BROWN PLASTIC JOINT	BKKH19009590S1	Aug 19, 2019
BROWN COATING ON WOOD	BKKH19007791S1	Jul 15, 2019
BROWN PLASTIC JOINT	BKKH19009590S1	Aug 19, 2019
<u>Lead in surface coating</u>		
LIGHT GREEN COATING ON WOOD	BKKH19008312S1	Jul 15, 2019
YELLOW COATING ON WOOD	BKKH19009836	Aug 15, 2019
LIGHT GREEN COATING ON WOOD	BKKH19008312S1	Jul 15, 2019
DARK GREEN COATING ON WOOD	BKKH20000806	Feb 12, 2020
BROWN PLASTIC JOINT	BKKH19009590S1	Aug 19, 2019
BROWN COATING ON WOOD	BKKH19007791S1	Jul 15, 2019
<u>Lead in substrate</u>		
BROWN PLASTIC JOINT	BKKH19009590S1	Aug 19, 2019
<u>Phthalate content</u>		
LIGHT GREEN COATING ON WOOD	BKKH19008312S1	Jul 15, 2019
YELLOW COATING ON WOOD	BKKH19009836	Aug 15, 2019
LIGHT GREEN COATING ON WOOD	BKKH19008312S1	Jul 15, 2019
DARK GREEN COATING ON WOOD	BKKH20000806	Feb 12, 2020
BROWN PLASTIC JOINT	BKKH19009590S1	Aug 19, 2019
BROWN COATING ON WOOD	BKKH19007791S1	Jul 15, 2019



TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH20000456

Test conducted:

1 Physical And Mechanical Tests

Test Standard : ASTM Standard Consumer Safety Specification for Toy Safety F963-17.

Age group for testing : For age over 2 years.

The submitted samples were undergone the use and abuse tests in accordance with the Federal Hazardous Substances Act (FHSA), Title 16, Code of Federal Regulations : -

Test	FHSA	Parameter
Drop test	Section 1500.52(b)	4 x 3.0 ft
Torque test	Section 1500.53(e)	4 in-lbf
Tension test	Section 1500.53(f)	15 lbf
Compression test	Section 1500.53(g)	30 lbf

Clause	Testing items	Assessment
4.1	Material quality	P
4.5	Sound-producing toys	NA
4.6.1	Toys intended for children under 36 months (small objects)	P
4.6.2 [▲]	Mouth-actuated toys	NA
4.6.3	Toys and games for 36 months to 72 months (small part warning)	NA
4.7	Accessible edges	P
4.8	Projections	NA
4.9	Accessible points	P
4.10	Wires or rods	NA
4.11	Nails and fasteners	NA
4.12	Plastic film	NA
4.13	Folding mechanisms and hinges	NA
4.14	Cords, straps and elastics	NA
4.15	Stability and over-load requirements	NA
4.16	Confined spaces	NA
4.17	Wheels, tires and axles	NA
4.18	Holes, clearance, and accessibility of mechanisms	NA
4.19	Simulated protective devices	NA
4.20(4.20.1 [▲])	Pacifiers	NA
4.21	Projectile toys	NA
4.22	Teethers and teething toys	NA

TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH20000456

Test conducted:

Clause	Testing items	Assessment
4.23	Rattles	NA
4.24	Squeeze toys	NA
4.25 (4.25.10, 4.25.11 [▲])	Battery-operated toys	NA
4.26	Toys intended to be attached to a crib or playpen	NA
4.27	Stuffed and beanbag-type toys	NA
4.28	Stroller and carriage toys	NA
4.29	Art materials	NA
4.30	Toy gun marking	NA
4.31	Balloons	NA
4.32	Certain toys with nearly spherical ends	NA
4.33	Marbles	NA
4.34	Balls	NA
4.35	Pompoms	NA
4.36	Hemispheric-shaped objects	NA
4.37 [▲]	Yoyo elastic tether toys	NA
4.38	Magnets	NA
4.39	Jaw entrapment in handles and steering wheels	NA
4.40	Expanding materials	NA
4.41	Toy chests	NA
5	Labelling requirement	P
6	Instructional literature	P
7	Producer's markings - name of producer and distributor (toy and package) - address (package)	Yes Yes

Remark : P = Pass NA = Not applicable

▲ = Tested items are not included in the TISI Accreditation

The submitted samples were undergone the tests in accordance with clause 8.5 through clause 8.17 and 8.19 through 8.26 on normal use, abuse and specific tests for different types of toys whichever is applicable.

Testing period : January 15, 2020 to January 21, 2020



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.



Number: BKKH20000456

Test conducted:

2 Flammability Test

Test Standard : Clause 4.2 of the ASTM Standard Consumer Safety Specification for Toy Safety F963-17.

Results : Did not ignite

Testing period : January 15, 2020 to January 21, 2020



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH20000456

Test conducted:

Heavy Elements Analysis

As per clause 4.3.5.1(2) of the ASTM Standard Consumer Safety Specification on Toy Safety F963-17, acid extraction method was used and heavy elements migration content were determined by ICP-OES analysis.

	<u>Result</u> <u>mg/kg</u>	<u>LOD</u> <u>mg/kg</u>	<u>LOQ</u> <u>mg/kg</u>	<u>Limit mg/kg</u>
(6)				
Sol. Barium (Ba)	ND	1	5	1000
Sol. Lead (Pb)	ND	1	5	90
Sol. Cadmium (Cd)	ND	1	5	75
Sol. Antimony (Sb)	ND	2	5	60
Sol. Selenium (Se)	ND	1	5	500
Sol. Chromium (Cr)	ND	2	5	60
Sol. Mercury (Hg)	ND	1	5	60
Sol. Arsenic (As)	ND	2	5	25

Remark: Sol. = Soluble
mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
LOD = Limit of Detection
ND = Not detected (Less than LOD)

LOQ = Limit of Quantitation
< = Less than

Tested components:

(6) = BROWN COATING ON WOOD Refer BKKH19007791S1

Note: The results of soluble toxic elements were adjusted by subtracting the analytical correction factor.



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.



Number: BKKH20000456

Test conducted:

Total Lead (Pb) Content

As per clause 4.3.5.1(1) of the ASTM Standard Consumer Safety Specification on Toy Safety F963-17, test method CPSC-CH-E1003-09.1:2011 was used and total Lead content was determined by ICP-OES analysis.

(I) Surface coating

<u>Tested Component</u>	<u>Result</u> <u>mg/kg</u>	<u>LOD</u> <u>(mg/kg)</u>	<u>LOQ</u> <u>(mg/kg)</u>	<u>Limit</u> <u>(mg/kg)</u>
(1)	ND	2	13	90
(2)	ND	2	13	90
(3)	ND	2	13	90
(4)	ND	2	13	90
(5)	ND	2	13	90
(6)	ND	2	13	90

Remark: mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
 LOD = Limit of Detection LOQ = Limit of Quantitation
 ND = Not detected (Less than LOD) < = Less than

Tested components:

- | | |
|-----------------------------------|----------------------|
| (1) = LIGHT GREEN COATING ON WOOD | Refer BKKH19008312S1 |
| (2) = YELLOW COATING ON WOOD | Refer BKKH19009836 |
| (3) = LIGHT GREEN COATING ON WOOD | Refer BKKH19008312S1 |
| (4) = DARK GREEN COATING ON WOOD | Refer BKKH20000806 |
| (5) = BROWN PLASTIC JOINT | Refer BKKH19009590S1 |
| (6) = BROWN COATING ON WOOD | Refer BKKH19007791S1 |



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH20000456

Test conducted:

Total Lead (Pb) Content

As per clause 4.3.5.2(2)(a) of the ASTM Standard Consumer Safety Specification on Toy Safety F963-17, test method CPSC-CH-E1001-08.3:2012, CPSC-CH-E1002-08.3:2012 were used and total Lead content was determined by ICP-OES analysis.

(II) Non-surface coating


<u>Tested Component</u>	<u>Result</u>	<u>LOD</u>	<u>LOQ</u>	<u>Limit</u>
(7)	mg/kg	(mg/kg)	(mg/kg)	(mg/kg)
	ND	1	13	100

Remark: mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
 LOD = Limit of Detection LOQ = Limit of Quantitation
 ND = Not detected (Less than LOD) < = Less than

Tested components:

(7) = BROWN PLASTIC JOINT

Refer BKKH19009590S1



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.



Number: BKKH20000456

Test conducted:

4 Total Lead (Pb) content[▲]
As per U.S. Code of Federal Regulations title 16 Part 1303. Acid digestion method was used and total Lead content was determined by Inductively Couple Plasma Optical Emission Spectrometry.

Tested component	Result %	LOD %	LOQ %	Limit %
(1)	ND	0.0002	0.0013	0.0090
(2)	ND	0.0002	0.0013	0.0090
(3)	ND	0.0002	0.0013	0.0090
(4)	ND	0.0002	0.0013	0.0090
(5)	ND	0.0002	0.0013	0.0090
(6)	ND	0.0002	0.0013	0.0090

Remark: % = percentage < = Less than
LOD = Limit of Detection LOQ = Limit of Quantitation
ND = Not detected (Less than LOD)
▲ = Tested items are not included in the TISI Accreditation

Tested components:

- (1) = LIGHT GREEN COATING ON WOOD Refer BKKH19008312S1
- (2) = YELLOW COATING ON WOOD Refer BKKH19009836
- (3) = LIGHT GREEN COATING ON WOOD Refer BKKH19008312S1
- (4) = DARK GREEN COATING ON WOOD Refer BKKH20000806
- (5) = BROWN PLASTIC JOINT Refer BKKH19009590S1
- (6) = BROWN COATING ON WOOD Refer BKKH19007791S1



TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.



Number: BKKH20000456

Test conducted:

5 Total lead (Pb) content in surface coating
As per U.S. Consumer Product Safety Improvement Act of 2008 (H.R. 4040), Title I, Section 101
for children’s products containing Lead, CPSC-CH-E1003-09.1:2011 method was used and total Lead
content was determined by Inductively Couple Plasma Optical Emission Spectrometry.

Table with 5 columns: Tested component, Result mg/kg, LOD mg/kg, LOQ mg/kg, Limit mg/kg. Rows 1-6 showing ND results and limits of 2 and 13 mg/kg.

Remark: mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
LOD = Limit of Detection LOD = Limit of Quantitation
ND = Not detected (Less than LOD) < = Less than

Tested components:

- (1) = LIGHT GREEN COATING ON WOOD Refer BKKH19008312S1
(2) = YELLOW COATING ON WOOD Refer BKKH19009836
(3) = LIGHT GREEN COATING ON WOOD Refer BKKH19008312S1
(4) = DARK GREEN COATING ON WOOD Refer BKKH20000806
(5) = BROWN PLASTIC JOINT Refer BKKH19009590S1
(6) = BROWN COATING ON WOOD Refer BKKH19007791S1



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.



Number: BKKH20000456

Test conducted:

6 Total lead (Pb) content in substrate material- non-metal children’s product
As per U.S. Consumer product safety improvement Act of 2008 (H.R. 4040), Title I, Section 101 for children’s products containing lead, CPSC-CH-E1002-08.3:2012 method was used and total lead content was determined by Inductively Couple Plasma Optical Emission Spectrometry.

<u>Tested component</u>	<u>Result</u>	<u>LOD</u>	<u>LOQ</u>	<u>Limit mg/kg</u>
	<u>mg/kg</u>	<u>mg/kg</u>	<u>mg/kg</u>	
(1)	ND	1	13	100

Remark: mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
 LOD = Limit of Detection LOQ = Limit of Quantitation
 ND = Not detected (Less than LOD) < = Less than

Tested components:

(1) = BROWN PLASTIC JOINT

Refer BKKH19009590S1



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH20000456

Test conducted:

7 Phthalate content

As per CPSC-CH-C1001-09.3:2010 and U.S. Consumer Product Safety Improvement Act 2008 (H.R. 4040), Title I, Section 108 requirement on Phthalates, solvent extraction method was used and Phthalate content was determined by Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

	<u>Result</u>					<u>LOD</u>	<u>LOQ</u>	<u>(16CFR1307)</u>	<u>NPR</u>
	(1)	(2)	(3)	(4)	(5)	(%, w/w)	(%, w/w)	Limit (%, w/w)	(%, w/w)
Dibutyl Phthalate (DBP)	ND	ND	ND	ND	ND	0.0015	0.0030	0.1	0.1
Di(2-ethylhexyl) phthalate (DEHP)	ND	ND	ND	ND	ND	0.0015	0.0030	0.1	0.1
Benzyl butyl Phthalate (BBP)	ND	ND	ND	ND	ND	0.0015	0.0030	0.1	0.1
Di-iso-nonyl Phthalate (DINP)	ND	ND	ND	ND	ND	0.0015	0.0090	0.1	0.1
Di-n-octyl Phthalate (DNOP)	ND	ND	ND	ND	ND	0.0015	0.0030	--	--
Di-iso-decyl Phthalate (DIDP)	ND	ND	ND	ND	ND	0.0015	0.0090	--	--
Di-isobutyl phthalate (DIBP)▲	ND	ND	ND	ND	ND	0.0015	0.0030	0.1	0.1
Di-n-pentyl phthalate (DPENP)▲	ND	ND	ND	ND	ND	0.0015	0.0030	0.1	0.1
Di-n-hexyl phthalate (DHEXP)▲	ND	ND	ND	ND	ND	0.0015	0.0030	0.1	0.1
Di-cyclohexyl phthalate (DCHP)▲	ND	ND	ND	ND	ND	0.0015	0.0030	0.1	0.1
Diisooctyl phthalate (DIOP)▲	ND	ND	ND	ND	ND	0.0015	0.0090	--	--

Remark : The above limit was quoted according to US 16 CFR Part 1307 for Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates except the Phthalate no.5-6,11 was conducted as per applicant requested only.

- NPR = Notice of proposed rulemaking
- %, w/w = Percentage weight by weight
- LOD = Limit of Detection
- LOQ = Limit of Quantitation
- ND = Not detected (Less than LOD)
- ▲ = Tested items are not included in the TISI Accreditation

Tested components:

(1) = LIGHT GREEN COATING ON WOOD	Refer	BKKH19008312S1
(2) = YELLOW COATING ON WOOD	Refer	BKKH19009836
(3) = LIGHT GREEN COATING ON WOOD	Refer	BKKH19008312S1
(4) = DARK GREEN COATING ON WOOD	Refer	BKKH20000806
(5) = BROWN PLASTIC JOINT	Refer	BKKH19009590S1



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH20000456

Test conducted:

Phthalate content

As per CPSC-CH-C1001-09.3:2010 and U.S. Consumer Product Safety Improvement Act 2008 (H.R. 4040), Title I, Section 108 requirement on Phthalates, solvent extraction method was used and Phthalate content was determined by Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

	<u>Result</u> <u>(%, w/w)</u>	<u>LOD</u> <u>(%, w/w)</u>	<u>LOQ</u> <u>(%, w/w)</u>	<u>(16CFR1307)</u> <u>Limit (%, w/w)</u>	<u>NPR</u> <u>(%, w/w)</u>
(6)					
Dibutyl Phthalate (DBP)	ND	0.0015	0.0030	0.1	0.1
Di(2-ethylhexyl) phthalate (DEHP)	ND	0.0015	0.0030	0.1	0.1
Benzyl butyl Phthalate (BBP)	ND	0.0015	0.0030	0.1	0.1
Di-iso-nonyl Phthalate (DINP)	ND	0.0015	0.0090	0.1	0.1
Di-n-octyl Phthalate (DNOP)	ND	0.0015	0.0030	--	--
Di-iso-decyl Phthalate (DIDP)	ND	0.0015	0.0090	--	--
Di-isobutyl phthalate (DIBP)▲	ND	0.0015	0.0030	0.1	0.1
Di-n-pentyl phthalate (DPENP)▲	ND	0.0015	0.0030	0.1	0.1
Di-n-hexyl phthalate (DHEXP)▲	ND	0.0015	0.0030	0.1	0.1
Di-cyclohexyl phthalate (DCHP)▲	ND	0.0015	0.0030	0.1	0.1
Diisooctyl phthalate (DIOP)▲	ND	0.0015	0.0090	--	--

Remark : The above limit was quoted according to US 16 CFR Part 1307 for Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates except the Phthalate no.5-6,11 was conducted as per applicant requested only.

- NPR = Notice of proposed rulemaking
- %, w/w = Percentage weight by weight
- LOD = Limit of Detection
- LOQ = Limit of Quantitation
- ND = Not detected (Less than LOD)
- ▲ = Tested items are not included in the TISI Accreditation

Tested components:

(6) = BROWN COATING ON WOOD

Refer BKKH19007791S1



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH20000456

Test conducted:

8 Phthalate content test[▲]

By solvent extraction and Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

	<u>Result</u>					<u>LOD</u>	<u>LOQ</u>	<u>Limit</u>
	(1)	(2)	(3)	(4)	(5)	(%, w/w)	(%, w/w)	(%, w/w)
Dibutyl Phthalate (DBP)	ND	ND	ND	ND	ND	0.0015	0.0030	0.1
Di(2-ethylhexyl) phthalate (DEHP)	ND	ND	ND	ND	ND	0.0015	0.0030	0.1
Benzyl butyl Phthalate (BBP)	ND	ND	ND	ND	ND	0.0015	0.0030	0.1
Di-iso-nonyl Phthalate (DINP)	ND	ND	ND	ND	ND	0.0015	0.0090	0.1
Diocetyl Phthalate (DNOP)	ND	ND	ND	ND	ND	0.0015	0.0030	0.1
Di-iso-decyl Phthalate (DIDP)	ND	ND	ND	ND	ND	0.0015	0.0090	0.1
Di-n-hexyl Phthalate (DnHP)	ND	ND	ND	ND	ND	0.0015	0.0030	0.1

Remark : %, w/w = Percentage weight by weight
 LOD = Limit of Detection
 LOQ = Limit of Quantitation
 ND = Not detected (Less than LOD)
 ▲ = Tested items are not included in the TISI Accreditation

Note : The above limit was quoted according to the California Proposition 65

Tested components:

(1) = LIGHT GREEN COATING ON WOOD	Refer	BKKH19008312S1
(2) = YELLOW COATING ON WOOD	Refer	BKKH19009836
(3) = LIGHT GREEN COATING ON WOOD	Refer	BKKH19008312S1
(4) = DARK GREEN COATING ON WOOD	Refer	BKKH20000806
(5) = BROWN PLASTIC JOINT	Refer	BKKH19009590S1



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH20000456

Test conducted:

Phthalate content test[▲]

By solvent extraction and Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

	<u>Result</u> (%, w/w)	<u>LOD</u> (%, w/w)	<u>LOQ</u> (%, w/w)	<u>Limit</u> (%, w/w)
(6)				
Dibutyl Phthalate (DBP)	ND	0.0015	0.0030	0.1
Di(2-ethylhexyl) phthalate (DEHP)	ND	0.0015	0.0030	0.1
Benzyl butyl Phthalate (BBP)	ND	0.0015	0.0030	0.1
Di-iso-nonyl Phthalate (DINP)	ND	0.0015	0.0090	0.1
Diocetyl Phthalate (DNOP)	ND	0.0015	0.0030	0.1
Di-iso-decyl Phthalate (DIDP)	ND	0.0015	0.0090	0.1
Di-n-hexyl Phthalate (DnHP)	ND	0.0015	0.0030	0.1

Remark : %, w/w = Percentage weight by weight
 LOD = Limit of Detection
 LOQ = Limit of Quantitation
 ND = Not detected (Less than LOD)
 ▲ = Tested items are not included in the TISI Accreditation

Note : The above limit was quoted according to the California Proposition 65

Tested components:

(6) = BROWN COATING ON WOOD

Refer BKKH19007791S1



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH20000456

Test conducted:

9 Total Lead (Pb) Content[▲]

As per Illinois Lead poisoning prevention act 410 ILCS 45 section 6 (public act 095-1019), acid digestion method was used and total Lead content was determined by Inductively Couple Plasma Optical Emission Spectrometry.

I Surface coating material

<u>Tested component</u>	<u>Result</u> mg/kg	<u>LOD</u> mg/kg	<u>LOQ</u> mg/kg	<u>Limit</u> mg/kg
(1)	ND	2	13	90
(2)	ND	2	13	90
(3)	ND	2	13	90
(4)	ND	2	13	90
(5)	ND	2	13	90
(6)	ND	2	13	90

Remark: < = Less than
mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
LOD = Limit of Detection
LOQ = Limit of Quantitation
ND = Not detected (Less than LOD)

Requirement: ▲ = Tested items are not included in the TISI Accreditation
According to Illinois Lead poisoning prevention act 410 ILCS 45 section 6 (public act 095-019), appropriate warning statement is required when the Lead content of the submitted sample is more than 40 ppm but less than 90 ppm for surface coatings and less than 100 ppm for substrates by total weight or a lower standard for Lead content as may be established by federal or state law or regulation.

Tested components:

- | | | |
|-----------------------------------|-------|----------------|
| (1) = LIGHT GREEN COATING ON WOOD | Refer | BKKH19008312S1 |
| (2) = YELLOW COATING ON WOOD | Refer | BKKH19009836 |
| (3) = LIGHT GREEN COATING ON WOOD | Refer | BKKH19008312S1 |
| (4) = DARK GREEN COATING ON WOOD | Refer | BKKH20000806 |
| (5) = BROWN PLASTIC JOINT | Refer | BKKH19009590S1 |
| (6) = BROWN COATING ON WOOD | Refer | BKKH19007791S1 |



TEST REPORT

The report shall not be reproduced without written approval from Intertek
The results relate only to the item tested.

Number: BKKH20000456

Test conducted:

II Non-surface coating material (substrate)

<u>Tested component</u>	<u>Result</u>	<u>LOD</u>	<u>LOQ</u>	<u>Limit</u>
(7)	<u>mg/kg</u>	<u>mg/kg</u>	<u>mg/kg</u>	<u>mg/kg</u>
	ND	1	13	100

Remark: < = Less than
mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million
LOD = Limit of Detection
LOQ = Limit of Quantitation
ND = Not detected (Less than LOD)

Requirement: According to Illinois Lead poisoning prevention act 410 ILCS 45 section 6 (public act 095-019), appropriate warning statement is required when the Lead content of the submitted sample is more than 40 ppm but less than 90 ppm for surface coatings and less than 100 ppm for substrates by total weight or a lower standard for Lead content as may be established by federal or state law or regulation.

Tested components:

(7) = BROWN PLASTIC JOINT Refer BKKH19009590S1

Note: LOD and LOQ value in this test report were effective since October, 2014

*****END*****/KS/NK

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our standard Terms and Conditions which can be obtained at our website: <http://www.intertek.com/terms/>. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. This report is made solely on the basis of your instructions and / or information and materials supplied by you and provide no warranty on the tested sample(s) be truly representative of the sample source. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. This report does not discharge or release you from your legal obligations and duties to any other person. You are the only one authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk. This report shall not be reproduced, except in full.

