

## TEST REPORT

The report shall not be reproduced without written approval from Intertek  
The results relate only to the item tested.

Number: BKKH17007954

Applicant: PLAN CREATIONS CO., LTD.  
8 MOO 8, TRANG-PALIAN RD.,  
YANTAKAO, TRANG, THAILAND 92140  
ATTN: K.SUPAPORN

Date: Aug 11, 2017

### Sample description:

Quantity of sample:	One (1) set
Sample description:	Wooden toy
Date sample received:	July 04, 2017
Date information received:	August 03, 2017

### Client Information:

One (1) set of submitted sample said to be PEEK-A-BOO ROLLER

Item Name:	PEEK-A-BOO ROLLER
Item Number:	5252



BKKH17007954

### Test conducted:

As requested by the applicant, for details please refer to attached page(s)

To be continued

Authorized by :  
For Intertek Testing Services (Thailand) Ltd.,  
Hardlines Laboratory

*Ladtaka W.*

Ladtaka Wongwiboonporn  
Laboratory Manager  
Hardlines Department

Page 1 of 21

## TEST REPORT

The report shall not be reproduced without written approval from Intertek  
The results relate only to the item tested.

Number: BKKH17007954

### Conclusion:

<u>Tested samples</u>	<u>Standard</u>	<u>Result</u>
Submitted sample	U.S. ASTM F963-16 for Physical and mechanical tests excluding labelling requirement of clause 5	Pass
	U.S. ASTM F963-16 for clause 4.5 Sound producing toys	Pass
	U.S. ASTM F963-16 for Flammability test of materials other than textile materials	Pass
	U.S. ASTM F963-11 and ASTM F963-16 for Heavy elements Test	Pass
	<u>Standard - U.S. CFR title 16</u> (CPSC regulations) Part 1303 total Lead content	Pass
	<u>Standard</u> U.S. Consumer product safety improvement Act 2008(H.R. 4040) Title I, Section 101 For total lead content in surface coating	Pass
	U.S. Consumer product safety improvement Act 2008(H.R. 4040) Title I, Section 101 For total lead content in non-surface coating material (substrate)	Pass
	U.S. Consumer product safety improvement Act 2008(H.R. 4040) Title I, Section 108 Requirement on phthalates	Pass
	Phthalate Content Requirement base on the California Proposition 65	Pass
	Illinois Lead Poisoning Prevention Act 410 ILCS 45 section 6 (public act 095-1019)	Pass

Remark: As requested by the applicant, the test was conducted only on components listed in this report.  
Other components were not tested.

\*\*\*\*\*

## TEST REPORT

The report shall not be reproduced without written approval from Intertek  
The results relate only to the item tested.

Number: BKKH17007954

**Remark:**

The chemical test results was not conducted on the below components of samples. Applicant claimed the components were tested on our previous test report.

<u>Components</u>	<u>Report No.</u>	<u>Date</u>
<u>ASTM F963-11: Heavy metal</u>		
LIGHT GRAY COATING ON WOOD	BKKH16015744	Nov 07, 2016
GRAY COATING ON WOOD (15744)	BKKH16015744	Nov 07, 2016
Gray coating on wood	BKKH16015641	Nov 07, 2016
Solid Wood	BKKH17000142	Jan 10, 2017
<u>ASTM F963-16: Heavy metal</u>		
BROWN COATING ON WOOD	BKKH17008463	Jul 14, 2017
WHITE COATING ON WOOD	BKKH17008950	Jul 26, 2017
LACQUER COATING ON WOOD	BKKH17008950	Jul 26, 2017
ORANGE COATING ON WOOD	BKKH17008552	Jul 18, 2017
YELLOW COATING ON WOOD	BKKH17008550	Jul 18, 2017
SKY BLUE COATING ON WOOD	BKKH17008550	Jul 18, 2017
<u>Lead in surface coating</u>		
LIGHT GRAY COATING ON WOOD	BKKH16015744	Nov 07, 2016
GRAY COATING ON WOOD (15744)	BKKH16015744	Nov 07, 2016
Gray coating on wood	BKKH16015641	Nov 07, 2016
BROWN COATING ON WOOD	BKKH17008463	Jul 14, 2017
WHITE COATING ON WOOD	BKKH17008950	Jul 26, 2017
LACQUER COATING ON WOOD	BKKH17008950	Jul 26, 2017
ORANGE COATING ON WOOD	BKKH17008552	Jul 18, 2017
YELLOW COATING ON WOOD	BKKH17008550	Jul 18, 2017
SKY BLUE COATING ON WOOD	BKKH17008550	Jul 18, 2017
<u>Lead in substrate</u>		
Solid Wood	BKKH17000142	Jan 10, 2017
<u>Phthalate content</u>		
LIGHT GRAY COATING ON WOOD	BKKH16015744	Nov 07, 2016
GRAY COATING ON WOOD (15744)	BKKH16015744	Nov 07, 2016
Gray coating on wood	BKKH16015641	Nov 07, 2016
BROWN COATING ON WOOD	BKKH17008463	Jul 14, 2017
WHITE COATING ON WOOD	BKKH17008950	Jul 26, 2017
LACQUER COATING ON WOOD	BKKH17008950	Jul 26, 2017
ORANGE COATING ON WOOD	BKKH17008552	Jul 18, 2017
YELLOW COATING ON WOOD	BKKH17008550	Jul 18, 2017
SKY BLUE COATING ON WOOD	BKKH17008550	Jul 18, 2017

\*\*\*\*\*



## TEST REPORT

The report shall not be reproduced without written approval from Intertek  
The results relate only to the item tested.

Number: BKKH17007954

Test conducted:

1 Physical And Mechanical Tests▲

Test Standard : ASTM Standard Consumer Safety Specification for Toy Safety F963-16.

Age group for testing : For age over 6 months.

The submitted samples were undergone the use and abuse tests in accordance with the Federal Hazardous Substances Act (FHSA), Title 16, Code of Federal Regulations : -

Test	FHSA	Parameter
Drop test	Section 1500.51(b)	10 x 4.5 ft
Torque test	Section 1500.53(e)	4 in-lbf
Tension test	Section 1500.53(f)	15 lbf
Compression test	Section 1500.53(g)	30 lbf

Clause	Testing items	Assessment
4.1	Material quality	P
4.5	Sound-producing toys	P *1
4.6.1	Toys intended for children under 36 months (small objects)	P
4.6.2	Mouth-actuated toys	NA
4.6.3	Toys and games for 36 months to 72 months (small part warning)	NA
4.7	Accessible edges	NA
4.8	Projections	NA
4.9	Accessible points	P
4.10	Wires or rods	NA
4.11	Nails and fasteners	NA
4.12	Plastic film	NA
4.13	Folding mechanisms and hinges	NA
4.14	Cords, straps and elastics	NA
4.15	Stability and over-load requirements	NA
4.16	Confined spaces	NA
4.17	Wheels, tires and axles	NA
4.18	Holes, clearance, and accessibility of mechanisms	NA
4.19	Simulated protective devices	NA
4.20	Pacifiers	NA
4.21	Projectile toys	NA
4.22	Teethers and teething toys	NA

## TEST REPORT

The report shall not be reproduced without written approval from Intertek  
The results relate only to the item tested.

Number: BKKH17007954

Test conducted:

Clause	Testing items	Assessment
4.23	Rattles	NA
4.24	Squeeze toys	NA
4.25	Battery-operated toys	NA
4.26	Toys intended to be attached to a crib or playpen	NA
4.27	Stuffed and beanbag-type toys	NA
4.28	Stroller and carriage toys	NA
4.29	Art materials	NA
4.30	Toy gun marking	NA
4.31	Balloons	NA
4.32	Certain toys with nearly spherical ends	NA
4.33	Marbles	NA
4.34	Balls	NA
4.35	Pompoms	NA
4.36	Hemispheric-shaped objects	NA
4.37	Yoyo elastic tether toys	NA
4.38	Magnets	NA
4.39	Jaw entrapment in handles and steering wheels	NA
4.40	Expanding materials	NA
4.41	Toy chests	NA
5	Labelling requirement	NA
6	Instructional literature	NA
7	Producer's markings - name of producer (toy) - address (toy)	Yes No

Remark : P = Pass NA = Not applicable

▲ = Tested items are not included in the TISI Accreditation

The submitted samples were undergone the tests in accordance with clause 8.5 through clause 8.17 and 8.19 through 8.26 on normal use, abuse and specific tests for different types of toys whichever is applicable.

The producer's name was found on the toy. However as specified in clause 7.1 of ASTM F963-16, the final product or its packaging must also be marked with the address.

Testing period : July 04, 2017 to July 12, 2017

\*\*\*\*\*

## TEST REPORT

The report shall not be reproduced without written approval from Intertek  
The results relate only to the item tested.

Number: BKKH17007954

Test conducted:

**\*1 Sound producing toys test**

Test Standard : ASTM Standard Consumer Safety Specification on Toy Safety F963-16, clause 4.5.

Clause	Test item	Assessment
4.5.1.1	A-weighted equivalent sound pressure level, $L_{Aeq}$ , produced by close to the ear toys.	NA
4.5.1.2	Maximum A-weighted sound pressure level, $L_{AFmax}$ , produced by the translational motion of floor or table top toys where the motion is imparted on the toy by the child.	NA
4.5.1.3	A-weighted equivalent sound pressure level, $L_{Aeq}$ , produced by all other toys.	P
4.5.1.4	C-weighted peak sound pressure level, $L_{Cpeak}$ , produced by close to the ear toys.	NA
4.5.1.5	C-weighted peak sound pressure level, $L_{Cpeak}$ , produced by any type of toy excluding toys using explosive action.	P
4.5.1.6	C-weighted peak sound pressure level, $L_{Cpeak}$ , produced by a toy using percussion caps or other explosive action.	NA

Remark : P = Pass NA = Not applicable

Measured data:

<u>Tested component</u>	<u>Equivalent sound pressure level (<math>L_{Aeq}</math>)</u>	<u>Limit (db)</u>
Peek-a-boo-roller	69.3	85

<u>Tested component</u>	<u>Peak sound pressure level (<math>L_{Cpeak}</math>)</u>	<u>Limit (db)</u>
Peek-a-boo-roller	88.3	115

Testing period : July 04, 2017 to July 12, 2017

\*\*\*\*\*

## TEST REPORT

The report shall not be reproduced without written approval from Intertek  
The results relate only to the item tested.

Number: BKKH17007954

Test conducted:

2 Flammability Test<sup>▲</sup>

Test Standard : Clause 4.2 of the ASTM Standard Consumer Safety Specification for Toy Safety F963-16.

Results : Did not ignite

Testing period : July 04, 2017 to July 12, 2017

\*\*\*\*\*

## TEST REPORT

The report shall not be reproduced without written approval from Intertek  
The results relate only to the item tested.

Number: BKKH17007954

Test conducted:

### 3 Heavy Elements Analysis

As per clause 4.3.5.1(2) of the ASTM Standard Consumer Safety Specification on Toy Safety F963-11 and F963-16<sup>▲</sup>, acid extraction method was used and heavy elements migration content were determined by ICP-OES analysis.

			<u>Result</u> <u>mg/kg</u>			<u>LOD</u> <u>mg/kg</u>	<u>LOQ</u> <u>mg/kg</u>	<u>Limit mg/kg</u>
	(1)	(2)	(3)	(4)	(5)			
Sol. Barium (Ba)	<4	<4	177	264	ND	1	5	1000
Sol. Lead (Pb)	ND	<4	ND	ND	ND	1	5	90
Sol. Cadmium (Cd)	ND	ND	ND	ND	ND	1	5	75
Sol. Antimony (Sb)	ND	ND	ND	ND	ND	2	5	60
Sol. Selenium (Se)	ND	ND	ND	ND	ND	1	5	500
Sol. Chromium (Cr)	ND	ND	ND	ND	ND	2	5	60
Sol. Mercury (Hg)	ND	ND	ND	ND	ND	1	5	60
Sol. Arsenic (As)	ND	ND	ND	ND	ND	2	5	25

Remark: Sol. = Soluble  
< = Less than  
mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million  
LOD = Limit of Detection  
LOQ = Limit of Quantitation  
ND = Not detected (Less than LOD)  
▲ = Tested items are not included in the TISI Accreditation

Tested components:

(1) =	LIGHT GRAY COATING ON WOOD	Refer	BKKH16015744
(2) =	GRAY COATING ON WOOD (15744)	Refer	BKKH16015744
(3) =	Gray coating on wood	Refer	BKKH16015641
(4) =	BROWN COATING ON WOOD	Refer	BKKH17008463
(5) =	WHITE COATING ON WOOD	Refer	BKKH17008950

Note: The results of soluble toxic elements were adjusted by subtracting the analytical correction factor.

\*\*\*\*\*



## TEST REPORT

The report shall not be reproduced without written approval from Intertek  
The results relate only to the item tested.

Number: BKKH17007954

Test conducted:

### Heavy Elements Analysis

As per clause 4.3.5.1(2) of the ASTM Standard Consumer Safety Specification on Toy Safety F963-11 and F963-16<sup>▲</sup>, acid extraction method was used and heavy elements migration content were determined by ICP-OES analysis.

			<u>Result</u> <u>mg/kg</u>		<u>LOD</u> <u>mg/kg</u>	<u>LOQ</u> <u>mg/kg</u>	<u>Limit mg/kg</u>
	(6)	(7)	(8)	(9)			
Sol. Barium (Ba)	ND	<5	ND	ND	1	5	1000
Sol. Lead (Pb)	ND	ND	ND	ND	1	5	90
Sol. Cadmium (Cd)	ND	ND	ND	ND	1	5	75
Sol. Antimony (Sb)	ND	ND	ND	ND	2	5	60
Sol. Selenium (Se)	ND	ND	ND	ND	1	5	500
Sol. Chromium (Cr)	ND	ND	ND	ND	2	5	60
Sol. Mercury (Hg)	ND	ND	ND	ND	1	5	60
Sol. Arsenic (As)	ND	ND	ND	ND	2	5	25

Remark: Sol. = Soluble  
< = Less than  
mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million  
LOD = Limit of Detection  
LOQ = Limit of Quantitation  
ND = Not detected (Less than LOD)  
▲ = Tested items are not included in the TISI Accreditation

Tested components:

(6) =	LACQUER COATING ON WOOD	Refer	BKKH17008950
(7) =	ORANGE COATING ON WOOD	Refer	BKKH17008552
(8) =	YELLOW COATING ON WOOD	Refer	BKKH17008550
(9) =	SKY BLUE COATING ON WOOD	Refer	BKKH17008550

Note: The results of soluble toxic elements were adjusted by subtracting the analytical correction factor.

\*\*\*\*\*

## TEST REPORT

The report shall not be reproduced without written approval from Intertek  
The results relate only to the item tested.

Number: BKKH17007954

Test conducted:

### Heavy Elements Analysis

As per clause 4.3.5.2(2)(b) of the ASTM Standard Consumer Safety Specification on Toy Safety F963-11 and F963-16<sup>▲</sup>, acid extraction method was used and heavy elements migration content were determined by ICP-OES analysis.

		<u>Result</u> <u>mg/kg</u>	<u>LOD</u> <u>mg/kg</u>	<u>LOQ</u> <u>mg/kg</u>	<u>Limit mg/kg</u>
	(10)				
Sol. Barium (Ba)	ND		1	5	1000
Sol. Lead (Pb)	ND		1	5	90
Sol. Cadmium (Cd)	ND		1	5	75
Sol. Antimony (Sb)	ND		2	5	60
Sol. Selenium (Se)	ND		1	5	500
Sol. Chromium (Cr)	ND		2	5	60
Sol. Mercury (Hg)	ND		1	5	60
Sol. Arsenic (As)	ND		2	5	25

Remark: Sol. = Soluble  
< = Less than  
mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million  
LOD = Limit of Detection  
LOQ = Limit of Quantitation  
ND = Not detected (Less than LOD)  
▲ = Tested items are not included in the TISI Accreditation

Tested components:

(10) = Solid Wood

Refer BKKH17000142

Note: The results of soluble toxic elements were adjusted by subtracting the analytical correction factor.

\*\*\*\*\*

## TEST REPORT

The report shall not be reproduced without written approval from Intertek

The results relate only to the item tested.

Number: BKKH17007954

Test conducted:

### Total Lead (Pb) Content

As per clause 4.3.5.1(1) of the ASTM Standard Consumer Safety Specification on Toy Safety F963-11 and F963-16<sup>▲</sup>, test method CPSC-CH-E1003-09.1:2011 was used and total Lead content was determined by ICP-OES analysis.

### (I) Surface coating

<u>Tested Component</u>	<u>Result</u> <u>mg/kg</u>	<u>LOD</u> <u>(mg/kg)</u>	<u>LOQ</u> <u>(mg/kg)</u>	<u>Limit</u> <u>(mg/kg)</u>
(1)	ND	2	13	90
(2)	ND	2	13	90
(3)	ND	2	13	90
(4)	ND	2	13	90
(5)	ND	2	13	90
(6)	ND	2	13	90
(7)	ND	2	13	90
(8)	ND	2	13	90
(9)	ND	2	13	90

Remark: mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million  
 LOD = Limit of Detection LOQ = Limit of Quantitation  
 ND = Not detected (Less than LOD) < = Less than  
 ▲ = Tested items are not included in the TISI Accreditation

### Tested components:

(1) =	LIGHT GRAY COATING ON WOOD	Refer	BKKH16015744
(2) =	GRAY COATING ON WOOD (15744)	Refer	BKKH16015744
(3) =	Gray coating on wood	Refer	BKKH16015641
(4) =	BROWN COATING ON WOOD	Refer	BKKH17008463
(5) =	WHITE COATING ON WOOD	Refer	BKKH17008950
(6) =	LACQUER COATING ON WOOD	Refer	BKKH17008950
(7) =	ORANGE COATING ON WOOD	Refer	BKKH17008552
(8) =	YELLOW COATING ON WOOD	Refer	BKKH17008550
(9) =	SKY BLUE COATING ON WOOD	Refer	BKKH17008550

\*\*\*\*\*



## TEST REPORT

The report shall not be reproduced without written approval from Intertek  
The results relate only to the item tested.

Number: BKKH17007954

Test conducted:

### Total Lead (Pb) Content<sup>▲</sup>

As per clause 4.3.5.2(2)(a) of the ASTM Standard Consumer Safety Specification on Toy Safety F963-11 and F963-16, test method CPSC-CH-E1001-08.3:2012, CPSC-CH-E1002-08.3:2012 were used and total Lead content was determined by ICP-OES analysis.

(II) Non-surface coating

<u>Tested Component</u>	<u>Result</u> <u>mg/kg</u>	<u>LOD</u> <u>(mg/kg)</u>	<u>LOQ</u> <u>(mg/kg)</u>	<u>Limit</u> <u>(mg/kg)</u>
(10)	ND	1	13	100

Remark: mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million  
 LOD = Limit of Detection LOQ = Limit of Quantitation  
 ND = Not detected (Less than LOD) < = Less than  
<sup>▲</sup> = Tested items are not included in the TISI Accreditation

Tested components:

(10) = Solid Wood

Refer BKKH17000142

\*\*\*\*\*

Number: BKKH17007954

Test conducted:

4 Total Lead (Pb) content<sup>▲</sup>

As per U.S. Code of Federal Regulations title 16 Part 1303. Acid digestion method was used and total Lead content was determined by Inductively Couple Plasma Optical Emission Spectrometry.

Tested component	Result %	LOD %	LOQ %	Limit %
(1)	ND	0.0002	0.0013	0.009
(2)	ND	0.0002	0.0013	0.009
(3)	ND	0.0002	0.0013	0.009
(4)	ND	0.0002	0.0013	0.009
(5)	ND	0.0002	0.0013	0.009
(6)	ND	0.0002	0.0013	0.009
(7)	ND	0.0002	0.0013	0.009
(8)	ND	0.0002	0.0013	0.009
(9)	ND	0.0002	0.0013	0.009

Remark:	% =	percentage	< =	Less than
	LOD =	Limit of Detection	LOQ =	Limit of Quantitation
	ND =	Not detected (Less than LOD)	< =	Less than
	▲ =	Tested items are not included in the TISI Accreditation		

Tested components:

(1) =	LIGHT GRAY COATING ON WOOD	Refer	BKKH16015744
(2) =	GRAY COATING ON WOOD (15744)	Refer	BKKH16015744
(3) =	Gray coating on wood	Refer	BKKH16015641
(4) =	BROWN COATING ON WOOD	Refer	BKKH17008463
(5) =	WHITE COATING ON WOOD	Refer	BKKH17008950
(6) =	LACQUER COATING ON WOOD	Refer	BKKH17008950
(7) =	ORANGE COATING ON WOOD	Refer	BKKH17008552
(8) =	YELLOW COATING ON WOOD	Refer	BKKH17008550
(9) =	SKY BLUE COATING ON WOOD	Refer	BKKH17008550

\*\*\*\*\*

## TEST REPORT

The report shall not be reproduced without written approval from Intertek  
The results relate only to the item tested.

Number: BKKH17007954

Test conducted:

5 Total lead (Pb) content in surface coating

As per U.S. Consumer Product Safety Improvement Act of 2008 (H.R. 4040), Title I, Section 101 for children's products containing Lead, CPSC-CH-E1003-09.1:2011 method was used and total Lead content was determined by Inductively Couple Plasma Optical Emission Spectrometry.

<u>Tested component</u>	<u>Result</u> <u>mg/kg</u>	<u>LOD</u> <u>mg/kg</u>	<u>LOQ</u> <u>mg/kg</u>	<u>Limit mg/kg</u>
(1)	ND	2	13	90
(2)	ND	2	13	90
(3)	ND	2	13	90
(4)	ND	2	13	90
(5)	ND	2	13	90
(6)	ND	2	13	90
(7)	ND	2	13	90
(8)	ND	2	13	90
(9)	ND	2	13	90

Remark: mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million  
LOD = Limit of Detection LOQ = Limit of Quantitation  
ND = Not detected (Less than LOD) < = Less than

Tested components:

(1) =	LIGHT GRAY COATING ON WOOD	Refer	BKKH16015744
(2) =	GRAY COATING ON WOOD (15744)	Refer	BKKH16015744
(3) =	Gray coating on wood	Refer	BKKH16015641
(4) =	BROWN COATING ON WOOD	Refer	BKKH17008463
(5) =	WHITE COATING ON WOOD	Refer	BKKH17008950
(6) =	LACQUER COATING ON WOOD	Refer	BKKH17008950
(7) =	ORANGE COATING ON WOOD	Refer	BKKH17008552
(8) =	YELLOW COATING ON WOOD	Refer	BKKH17008550
(9) =	SKY BLUE COATING ON WOOD	Refer	BKKH17008550

\*\*\*\*\*

## TEST REPORT

The report shall not be reproduced without written approval from Intertek  
The results relate only to the item tested.

Number: BKKH17007954

Test conducted:

- 6 Total lead (Pb) content in substrate material- non-metal children's product <sup>▲</sup>  
As per U.S. Consumer product safety improvement Act of 2008 (H.R. 4040), Title I, Section 101 for children's products containing lead, CPSC-CH-E1002-08.3:2012 method was used and total lead content was determined by Inductively Couple Plasma Optical Emission Spectrometry.

<u>Tested component</u>	<u>Result</u> <u>mg/kg</u>	<u>LOD</u> <u>mg/kg</u>	<u>LOQ</u> <u>mg/kg</u>	<u>Limit mg/kg</u>
(1)	ND	1	13	100

Remark: mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million  
LOD = Limit of Detection LOQ = Limit of Quantitation  
ND = Not detected (Less than LOD) < = Less than  
<sup>▲</sup> = Tested items are not included in the TISI Accreditation

Tested components:

(1) = Solid Wood Refer BKKH17000142

\*\*\*\*\*

## TEST REPORT

The report shall not be reproduced without written approval from Intertek  
The results relate only to the item tested.

Number: BKKH17007954

Test conducted:

### 7 Phthalate content

As per CPSC-CH-C1001-09.3:2010 and U.S. Consumer Product Safety Improvement Act 2008 (H.R. 4040), Title I, Section 108 requirement on Phthalates, solvent extraction method was used and Phthalate content was determined by Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

	Result (%, w/w)					LOD (%, w/w)	LOQ (%, w/w)	Limit (%, w/w)	NPR (%, w/w)
	(1)	(2)	(3)	(4)	(5)				
Dibutyl Phthalate (DBP)	ND	ND	ND	ND	ND	0.0015	0.003	0.1	0.1
Diethyl hexyl Phthalate (DEHP)	ND	ND	ND	ND	ND	0.0015	0.003	0.1	0.1
Benzyl butyl Phthalate (BBP)	ND	ND	ND	ND	ND	0.0015	0.003	0.1	0.1
Di-iso-nonyl Phthalate (DINP)	ND	ND	ND	ND	ND	0.0015	0.009	0.1	0.1
Di-n-octyl Phthalate (DNOP)	ND	ND	ND	ND	ND	0.0015	0.003	0.1	--
Di-iso-decyl Phthalate (DIDP)	ND	ND	ND	ND	ND	0.0015	0.009	0.1	--
Di-isobutyl phthalate (DIBP) <sup>▲</sup>	ND	ND	ND	ND	ND	0.0015	0.009	--	0.1
Di-n-pentyl phthalate (DnPP) <sup>▲</sup>	ND	ND	ND	ND	ND	0.0015	0.009	--	0.1
Di-n-hexyl phthalate (DnHP) <sup>▲</sup>	ND	ND	ND	ND	ND	0.0015	0.009	--	0.1
Di-cyclohexyl phthalate (DCHP) <sup>▲</sup>	ND	ND	ND	ND	ND	0.0015	0.009	--	0.1
Diisooctyl phthalate (DIOP) <sup>▲</sup>	ND	ND	ND	ND	ND	0.0015	0.009	--	--

Remark : The above limit was quoted according to US Consumer Product Safety Improvement Act 2008 for prohibition on sale of certain products containing specified phthalates.

NPR = Notice of proposed rulemaking

%, w/w = Percentage weight by weight

LOD = Limit of Detection

LOQ = Limit of Quantitation

ND = Not detected (Less than LOD)

▲ = Tested items are not included in the TISI Accreditation

Tested components:

(1) =	LIGHT GRAY COATING ON WOOD	Refer	BKKH16015744
(2) =	GRAY COATING ON WOOD (15744)	Refer	BKKH16015744
(3) =	Gray coating on wood	Refer	BKKH16015641
(4) =	BROWN COATING ON WOOD	Refer	BKKH17008463
(5) =	WHITE COATING ON WOOD	Refer	BKKH17008950

\*\*\*\*\*





## TEST REPORT

The report shall not be reproduced without written approval from Intertek  
The results relate only to the item tested.

Number: BKKH17007954

Test conducted:

### Phthalate content

As per CPSC-CH-C1001-09.3:2010 and U.S. Consumer Product Safety Improvement Act 2008 (H.R. 4040), Title I, Section 108 requirement on Phthalates, solvent extraction method was used and Phthalate content was determined by Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

	Result (%, w/w)				LOD (%, w/w)	LOQ (%, w/w)	Limit (%, w/w)	NPR (%, w/w)
	(6)	(7)	(8)	(9)				
Dibutyl Phthalate (DBP)	ND	ND	ND	ND	0.0015	0.003	0.1	0.1
Diethyl hexyl Phthalate (DEHP)	ND	ND	ND	ND	0.0015	0.003	0.1	0.1
Benzyl butyl Phthalate (BBP)	ND	ND	ND	ND	0.0015	0.003	0.1	0.1
Di-iso-nonyl Phthalate (DINP)	ND	ND	ND	ND	0.0015	0.009	0.1	0.1
Di-n-octyl Phthalate (DNOP)	ND	ND	ND	ND	0.0015	0.003	0.1	--
Di-iso-decyl Phthalate (DIDP)	ND	ND	ND	ND	0.0015	0.009	0.1	--
Di-isobutyl phthalate (DIBP) <sup>▲</sup>	ND	ND	ND	ND	0.0015	0.009	--	0.1
Di-n-pentyl phthalate (DnPP) <sup>▲</sup>	ND	ND	ND	ND	0.0015	0.009	--	0.1
Di-n-hexyl phthalate (DnHP) <sup>▲</sup>	ND	ND	ND	ND	0.0015	0.009	--	0.1
Di-cyclohexyl phthalate (DCHP) <sup>▲</sup>	ND	ND	ND	ND	0.0015	0.009	--	0.1
Diisooctyl phthalate (DIOP) <sup>▲</sup>	ND	ND	ND	ND	0.0015	0.009	--	--

Remark : The above limit was quoted according to US Consumer Product Safety Improvement Act 2008 for prohibition on sale of certain products containing specified phthalates.

NPR = Notice of proposed rulemaking

%, w/w = Percentage weight by weight

LOD = Limit of Detection

LOQ = Limit of Quantitation

ND = Not detected (Less than LOD)

▲ = Tested items are not included in the TISI Accreditation

Tested components:

(6) =	LACQUER COATING ON WOOD	Refer	BKKH17008950
(7) =	ORANGE COATING ON WOOD	Refer	BKKH17008552
(8) =	YELLOW COATING ON WOOD	Refer	BKKH17008550
(9) =	SKY BLUE COATING ON WOOD	Refer	BKKH17008550

\*\*\*\*\*

## TEST REPORT

The report shall not be reproduced without written approval from Intertek  
The results relate only to the item tested.

Number: BKKH17007954

Test conducted:

### 8 Phthalate content test<sup>▲</sup>

By solvent extraction and Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

	Result (%, w/w)					LOD (%, w/w)	LOQ (%, w/w)	Limit (%, w/w)
	(1)	(2)	(3)	(4)	(5)			
Dibutyl Phthalate (DBP)	ND	ND	ND	ND	ND	0.0015	0.003	0.1
Diethyl hexyl Phthalate (DEHP)	ND	ND	ND	ND	ND	0.0015	0.003	0.1
Benzyl butyl Phthalate (BBP)	ND	ND	ND	ND	ND	0.0015	0.003	0.1
Di-iso-nonyl Phthalate (DINP)	ND	ND	ND	ND	ND	0.0015	0.009	0.1
Dioctyl Phthalate (DNOP)	ND	ND	ND	ND	ND	0.0015	0.003	0.1
Di-iso-decyl Phthalate (DIDP)	ND	ND	ND	ND	ND	0.0015	0.009	0.1
Di-n-hexyl Phthalate (DnHP)	ND	ND	ND	ND	ND	0.0015	0.003	0.1

Remark :      %, w/w = Percentage weight by weight

LOD = Limit of Detection

LOQ = Limit of Quantitation

ND = Not detected (Less than LOD)

▲ = Tested items are not included in the TISI Accreditation

Note :      The above limit was quoted according to the California Proposition 65

Tested components:

(1) =	LIGHT GRAY COATING ON WOOD	Refer	BKKH16015744
(2) =	GRAY COATING ON WOOD (15744)	Refer	BKKH16015744
(3) =	Gray coating on wood	Refer	BKKH16015641
(4) =	BROWN COATING ON WOOD	Refer	BKKH17008463
(5) =	WHITE COATING ON WOOD	Refer	BKKH17008950

\*\*\*\*\*

## TEST REPORT

The report shall not be reproduced without written approval from Intertek  
The results relate only to the item tested.

Number: BKKH17007954

Test conducted:

### Phthalate content test<sup>▲</sup>

By solvent extraction and Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

	Result (%, w/w)				LOD (%, w/w)	LOQ (%, w/w)	Limit (%, w/w)
	(6)	(7)	(8)	(9)			
Dibutyl Phthalate (DBP)	ND	ND	ND	ND	0.0015	0.003	0.1
Diethyl hexyl Phthalate (DEHP)	ND	ND	ND	ND	0.0015	0.003	0.1
Benzyl butyl Phthalate (BBP)	ND	ND	ND	ND	0.0015	0.003	0.1
Di-iso-nonyl Phthalate (DINP)	ND	ND	ND	ND	0.0015	0.009	0.1
Dioctyl Phthalate (DNOP)	ND	ND	ND	ND	0.0015	0.003	0.1
Di-iso-decyl Phthalate (DIDP)	ND	ND	ND	ND	0.0015	0.009	0.1
Di-n-hexyl Phthalate (DnHP)	ND	ND	ND	ND	0.0015	0.003	0.1

Remark :      %, w/w = Percentage weight by weight

LOD = Limit of Detection

LOQ = Limit of Quantitation

ND = Not detected (Less than LOD)

▲ = Tested items are not included in the TISI Accreditation

Note :      The above limit was quoted according to the California Proposition 65

Tested components:

(6) =	LACQUER COATING ON WOOD	Refer	BKKH17008950
(7) =	ORANGE COATING ON WOOD	Refer	BKKH17008552
(8) =	YELLOW COATING ON WOOD	Refer	BKKH17008550
(9) =	SKY BLUE COATING ON WOOD	Refer	BKKH17008550

\*\*\*\*\*

## TEST REPORT

The report shall not be reproduced without written approval from Intertek  
The results relate only to the item tested.

Number: BKKH17007954

Test conducted:

### 9 Total Lead (Pb) Content <sup>▲</sup>

As per Illinois Lead poisoning prevention act 410 ILCS 45 section 6 (public act 095-1019), acid digestion method was used and total Lead content was determined by Inductively Couple Plasma Optical Emission Spectrometry.

#### I Surface coating material

<u>Tested component</u>	<u>Result</u> <u>mg/kg</u>	<u>LOD</u> <u>mg/kg</u>	<u>LOQ</u> <u>mg/kg</u>	<u>Limit</u> <u>mg/kg</u>
(1)	ND	2	13	90
(2)	ND	2	13	90
(3)	ND	2	13	90
(4)	ND	2	13	90
(5)	ND	2	13	90
(6)	ND	2	13	90
(7)	ND	2	13	90
(8)	ND	2	13	90
(9)	ND	2	13	90

Remark: < = Less than  
mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million  
LOD = Limit of Detection  
LOQ = Limit of Quantitation  
ND = Not detected (Less than LOD)  
<sup>▲</sup> = Tested items are not included in the TISI Accreditation

Requirement: According to Illinois Lead poisoning prevention act 410 ILCS 45 section 6 (public act 095-019), appropriate warning statement is required when the Lead content of the submitted sample is more than 40 ppm but less than 90 ppm for surface coatings and less than 100 ppm for substrates by total weight or a lower standard for Lead content as may be established by federal or state law or regulation.

#### Tested components:

(1) =	LIGHT GRAY COATING ON WOOD	Refer	BKKH16015744
(2) =	GRAY COATING ON WOOD (15744)	Refer	BKKH16015744
(3) =	Gray coating on wood	Refer	BKKH16015641
(4) =	BROWN COATING ON WOOD	Refer	BKKH17008463
(5) =	WHITE COATING ON WOOD	Refer	BKKH17008950
(6) =	LACQUER COATING ON WOOD	Refer	BKKH17008950
(7) =	ORANGE COATING ON WOOD	Refer	BKKH17008552
(8) =	YELLOW COATING ON WOOD	Refer	BKKH17008550
(9) =	SKY BLUE COATING ON WOOD	Refer	BKKH17008550

\*\*\*\*\*

## TEST REPORT

The report shall not be reproduced without written approval from Intertek  
The results relate only to the item tested.

Number: BKKH17007954

Test conducted:

II Non-surface coating material (substrate)

<u>Tested component</u>	<u>Result</u>	<u>LOD</u>	<u>LOQ</u>	<u>Limit</u>
	<u>mg/kg</u>	<u>mg/kg</u>	<u>mg/kg</u>	<u>mg/kg</u>
(10)	ND	1	13	100

Remark: < = Less than  
mg/kg = Milligram per kilogram based on weight of sample; = ppm = Parts per million  
LOD = Limit of Detection  
LOQ = Limit of Quantitation  
ND = Not detected (Less than LOD)

Requirement: According to Illinois Lead poisoning prevention act 410 ILCS 45 section 6 (public act 095-019), appropriate warning statement is required when the Lead content of the submitted sample is more than 40 ppm but less than 90 ppm for surface coatings and less than 100 ppm for substrates by total weight or a lower standard for Lead content as may be established by federal or state law or regulation.

Tested components:

(10) = Solid Wood

Refer BKKH17000142

Note: LOD and LOQ value in this test report were effective since October, 2014

\*\*\*\*\*END\*\*\*\*\*/KS/ST

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our standard Terms and Conditions which can be obtained at our website: <http://www.intertek.com/terms/>. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. This report is made solely on the basis of your instructions and / or information and materials supplied by you and provide no warranty on the tested sample(s) be truly representative of the sample source. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. This report does not discharge or release you from your legal obligations and duties to any other person. You are the only one authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk.  
This report shall not be reproduced, except in full.